

First edition
2007-12-15

AMENDMENT 1
2012-09-15

**Protective clothing for protection against
chemicals — Classification, labelling and
performance requirements —**

AMENDMENT 1

*Vêtements de protection contre les produits chimiques — Classification,
étiquetage et exigences de performances —*

AMENDEMENT 1

STANDARDSISO.COM : Click to view the full PDF of ISO 16602:2007/Amd 1:2012



Reference number
ISO 16602:2007/Amd.1:2012(E)

STANDARDSISO.COM : Click to view the full PDF of ISO 16602:2007/Amd 1:2012



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 16602:2007 was prepared by Technical Committee ISO/TC 94, *Personal safety — Protective clothing and equipment*, Subcommittee SC 13, *Protective clothing*.

STANDARDSISO.COM : Click to view the full PDF of ISO 16602:2007/Amd.1:2012

STANDARDSISO.COM : Click to view the full PDF of ISO 16602:2007/Amd 1:2012

Protective clothing for protection against chemicals — Classification, labelling and performance requirements —

AMENDMENT 1

Page v, Introduction

Add the following after the last paragraph:

Changes introduced by Amendment 1:

- Experimental work has shown that the test method to assess flammability of chemical protective clothing materials was not suitable for some materials used for this purpose. Since it was not possible to reach a good reproducibility of test results, it was decided to remove this test requirement from this International Standard.
- The references to ISO 17491:2002 have been replaced by references to four new parts of ISO 17491.
- Some editorial changes have been made in 5.10, A.1, A.3, G.3 and G.6 in order to achieve a better, unambiguous understanding of the requirements in these clauses.
- In 6.5.1 and 6.5.2 the specifications for the reporting of test results has been improved.
- Errors in 6.6, 6.14, 7.5.2, 7.6.5 and G.6 have been corrected.

Page 2, Normative references

Delete:

EN 13274-4:2001, *Respiratory protective devices — Methods of test — Part 4: Flame tests*

ISO 17491:2002, *Protective clothing — Protection against gaseous and liquid chemicals — Determination of resistance of protective clothing to penetration by liquids and gases*

Add:

ISO 17491-1:2012, *Protective clothing — Test methods for clothing providing protection against chemicals — Part 1: Determination of resistance to outward leakage of gases (internal pressure test)*

ISO 17491-2:2012, *Protective clothing — Test methods for clothing providing protection against chemicals — Part 2: Determination of resistance to inward leakage of aerosols and gases (inward leakage test)*

ISO 17491-3:2008, *Protective clothing — Test methods for clothing providing protection against chemicals — Part 3: Determination of resistance to penetration by a jet of liquid (jet test)*

ISO 17491-4:2008, *Protective clothing — Test methods for clothing providing protection against chemicals — Part 4: Determination of resistance to penetration by a spray of liquid (spray test)*

Page 7, 5.4 Leak tightness

Replace the existing subclause with the following:

When tested in accordance with ISO 17491-1:2012, Method 2, Type 1a, Type 1b and Type 1c chemical protective suits shall not have a pressure drop of more than 20 % after the pressure/inflation period. Leak tightness testing shall be performed on two chemical protective suits.

Page 7, 5.5 *Inward leakage*

Replace the existing subclause with the following:

When tested for inward leakage as specified in ISO 17491-2:2012, Method 1 or 2, Type 1c and Type 2 chemical protective suits shall not have an inward leakage greater than 0,05 %. Type 1b chemical protective suits shall be tested for inward leakage when the facemask is not permanently joined to the suit, and shall not have an inward leakage greater than 0,05 % in the ocular cavity of the mask. Inward leakage testing shall be performed on two sample clothing items. A separate test subject shall be used for each test.

Page 7, 5.6 *Liquid penetration resistance (jet test)*

Replace the existing subclause with the following:

Type 3 chemical protective clothing shall be conditioned by wearing according to Procedure C of Annex A and, when subsequently tested for liquid penetration resistance using a jet test in accordance with ISO 17491-3:2008, shall show no penetration greater than three times the total calibrated stain area. Liquid penetration resistance testing shall be performed on two sample clothing items using a separate test subject for each test.

Page 7, 5.7 *Liquid penetration resistance (spray test)*

Replace the existing subclause with the following:

Type 4 chemical protective clothing shall be conditioned by wearing according to Procedure C of Annex A and, when subsequently tested for liquid penetration resistance using a spray test in accordance with ISO 17491-4:2008, Method B, shall show no penetration greater than three times the total calibrated stain area. Liquid penetration resistance testing shall be performed on two sample clothing items using a separate test subject for each test.

Page 8, 5.9 *Limited liquid penetration resistance (modified spray test)*

Replace the existing subclause with the following:

Type 6 chemical protective clothing shall be conditioned by wearing according to Procedure C of Annex A and, when subsequently tested for limited liquid penetration resistance using a modified spray test in accordance with ISO 17491-4:2008, Method A, using a 1 min exposure, shall show no penetration greater than three times the total calibrated stain area. Liquid penetration resistance testing shall be performed on two sample clothing items using a separate test subject for each test.

Page 8, 5.10 *Practical performance*

Replace the text of list item b) with the following:

During the practical performance test, the test subject shall be asked to read a sign with the dimensions of 100 mm high and 200 mm wide at a distance of 6 m; on the sign there shall be four randomly selected letters of proportional font so that they fill the sign. For chemical protective clothing with hoods that are not at a fixed distance from the wearer's eyes, the hood/visor shall be worn in the typical wearing position.

Page 9, 5.11 Face piece

Replace the third paragraph with the following:

If the face piece is attached to a Type 1b chemical protective suit in a non-permanent manner, the sealing mechanism shall be tested for liquid penetration resistance using a jet test in accordance with ISO 17491-3:2008, and shall show no penetration greater than three times the calibrated stain area. Two samples of face piece to suit joints shall be tested after temperature conditioning (see 5.2).

Page 13, Table 3

Delete the reference to subclause 6.16 as follows:

Sub-clause	Specific requirement	Type of chemical protective clothing								
		1	2	3	4	5	6	7	8	9
6.16	Resistance to flame	×	×	×	×	×	×	×	—	×

Page 14, 6.5.1 General

Replace the second paragraph with the following:

Materials used in Types 1, 2 and 3 chemical protective clothing shall achieve at least Class 3 performance against at least one of the chemicals listed in ISO 6529:2001, Annex A. The results shall be reported in the manufacturer's product technical information as specified in 10.3, together with a statement indicating whether the results have been obtained by closed loop testing or open loop testing.

Page 14, 6.5.1 General

Replace the fifth paragraph with the following:

Materials used in Type 4 chemical protective clothing – unless tested and classified according to 6.6 for resistance to penetration by liquid under pressure – shall achieve at least permeation resistance Class 1 performance against the specific chemicals indicated by the manufacturer. The results shall be reported in the manufacturer's product technical information as specified in 10.3, together with a statement indicating whether the results have been obtained by closed loop testing or open loop testing.

Page 14, 6.5.2 Classification of permeation resistance by breakthrough time (optional)

Replace the first paragraph with the following:

In addition to classifying the permeation resistance of the chemical protective clothing material according to average time to reach a cumulative permeation of 150 µg/cm², the option of classifying the material according to the normalized breakthrough time using a permeation rate of 0,1 µg/cm²min, or the normalized breakthrough time using a permeation rate of 1,0 µg/cm²min, or both normalized breakthrough times, may be chosen. The chemical protective clothing material average normalized breakthrough times shall be classified according to the levels of performance provided in Table 5. The results shall be reported in the manufacturer's product technical information as specified in 10.3, together with a statement indicating whether the results have been obtained by closed loop testing or open loop testing.

Page 15, 6.6 Resistance to penetration by liquid under pressure

In the first line, replace “ISO 13994:2005, Method E” with “ISO 13994:2005, Procedure D”.

Page 19, 6.14 Abrasion resistance

Replace the first paragraph with the following:

When tested in accordance with ISO 12947-2 in the inverted mode, i.e. a test specimen of at least 140mm diameter placed on the abradant table and an abradant of at least 30mm diameter mounted in the test piece holder, using abrasive paper specified in Annex F and with an applied pressure of 9 kPa, the chemical protective clothing material abrasion resistance shall be classified using the number of abrasion cycles which cause damage to the material according to the levels of performance provided in Table 14. Four specimens shall be tested and the performance classified according to the lowest single result.

Page 21, 6.16 Resistance to flame

Delete the entire subclause.

Page 23, 7.5.2 Seam strength

Renumber the existing Table 18 as Table 17.

Page 24, 7.6.5 Resistance to ignition

Delete the entire subclause.

Page 27, 10.4 Other test information

Add the following after the first paragraph:

If the garment is flame retardant, this shall be shown by test results obtained with a suitable test method. If the garment is not claimed to be flame retardant, the product information shall contain the warning: “Flammable. Keep away from fire.”

NOTE For example, ISO 14116 specifies the performance requirements for the limited flame spread properties of materials, material assemblies and protective clothing in order to reduce the possibility of the clothing burning and thereby itself constituting a hazard. The classification system is based on testing according to ISO 15025:2000. Previous, less severe minimum requirements for resistance to ignition or resistance to flame of clothing materials, visors, etc., were based on test results in EN 13274-4, Method 3, which however has been found unsuitable for assessing flame retardance.

Page 28, A.1 Procedure A

Replace list item d) with the following:

Stand erect with the arms down at the side of the body. Raise extended arms in the lateral direction on either side of the body upwards until the arms are vertical. Then bend the arms at elbows so that the upper arm is still vertical while the lower arm is horizontal, with the wrists backwards above the head. Repeat exercise four times. Then stand again erect with the arms down at the side of the body. Raise extended arms forward upwards until the arms are vertical. Then bend the arms at the elbows so that the upper