
Shaped insulating refractory products — Classification

Produits réfractaires isolants façonnés — Classification

STANDARDSISO.COM : Click to view the full PDF of ISO 2245:2006



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 2245:2006

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2245 was prepared by Technical Committee ISO/TC 33, *Refractories*.

This third edition cancels and replaces the second edition (ISO 2245:1990), Clauses 3 and 5 and Tables 1 and 2 of which have been technically revised.

Shaped insulating refractory products — Classification

1 Scope

This International Standard specifies a classification of shaped insulating refractory products, based on the determination of permanent change in dimension on heating, with a secondary classification based on bulk density to cover lightweight products (Class L). Products composed of ceramic fibres are excluded.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 836: 2001, *Terminology for refractories*

ISO 5016, *Shaped insulating refractory products — Determination of bulk density and true porosity*

ISO 2477, *Shaped insulating refractory products — Determination of permanent change in dimensions on heating*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 836 and the following apply.

3.1

shaped insulating refractory product

shaped insulating refractory

shaped refractory having a true porosity of not less than 45 % by volume

NOTE 1 Adapted from ISO 836:2001.

NOTE 2 The true porosity is determined in accordance with ISO 5016.

NOTE 3 These products are characterized by low thermal conductivity and low heat capacity.

4 Classification

Shaped insulating refractory products are subdivided into groups according to:

- a) the temperature at which the permanent change in dimensions, determined in accordance with ISO 2477, is 2 % or less (see Table 1);
- b) the bulk density, rounded to two decimal places, determined in accordance with ISO 5016, to distinguish Class L products from those with the same grouping according to a), but with a higher porosity. Products with average bulk densities equal to or below that given in Table 2 shall be designated as Class L.

For the determination of bulk density, the test pieces should be large enough for the desired accuracy to be attained. The determination shall be carried out in accordance with ISO 5016, except that the dimensions shall be measured to within $\pm 0,1$ mm using callipers.

Table 1 — Classification by temperature

Group	Temperature at which the test of permanent change in dimensions is carried out °C
75	750
80	800
85	850
90	900
95	950
100	1 000
105	1 050
110	1 100
115	1 150
120	1 200
125	1 250
130	1 300
135	1 350
140	1 400
150	1 500
160	1 600
170	1 700
180	1 800
NOTE The temperatures given as limits for the groups according to the permanent change in dimension of the products are not necessarily the limit temperatures of use, as the behaviour of products in service depends not only on the temperature, but also on the conditions of use.	

Table 2 — Classification by bulk density

Group	Maximum average bulk density ^a of class L products g/cm ³ ^b
75	0,40
80	0,50
85	0,55
90	0,60
95	0,65
100	0,65
105	0,65
110	0,70
115	0,70
120	0,70
125	0,75
130	0,80
135	0,85
140	0,90
150	0,95
160	1,15
170	1,35
180	1,60
^a In each group of class L, the bulk density is considered only as a distinguishing property and is given to two decimal places. ^b 1 g/cm ³ = 10 ³ kg/m ³ .	

5 Designation

A shaped insulating product shall be designated by:

- a) a reference to this International Standard;
- b) the group to which it belongs;
- c) an indication of its bulk density;
- d) the fact that it belongs to class L (where applicable).

EXAMPLE 1

Shaped insulating product in accordance with ISO 2245, group to which it belongs (120), bulk density (0,8):

ISO 2245-120-0,8

EXAMPLE 2

Shaped insulating product in accordance with ISO 2245, group to which it belongs (140), bulk density (1,2):

ISO 2245-140-1,2

EXAMPLE 3

Shaped insulating product in accordance with ISO 2245, group to which it belongs (80), bulk density (0,5) and, if applicable, the fact that it belongs to class L:

ISO 2245-80-0,5-L

EXAMPLE 4

Shaped insulating product in accordance with ISO 2245, group to which it belongs (140), bulk density (0,80) and, if applicable, the fact that it belongs to class L:

ISO 2245-140-0,80-L

STANDARDSISO.COM : Click to view the full PDF of ISO 2245:2006