
**Plastics — Joining of thermoplastic
moulded components — Specification
of variables for thermal joining
processes**

*Plastiques — Assemblage de composants thermoplastiques moulés —
Spécification de variables pour les procédés d'assemblage thermique*

STANDARDSISO.COM : Click to view the full PDF of ISO 23512:2021



STANDARDSISO.COM : Click to view the full PDF of ISO 23512:2021



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Technical content of thermal joining process specification (TJPS)	3
4.1 General	3
4.2 Related to the joining organization	3
4.3 Related to the sub-component(s)	3
4.4 Common to all joining processes	3
4.5 Specific to a joining process	4
4.5.1 Ultrasonic welding/staking/spot welding	4
4.5.2 Infrared welding	4
4.5.3 Hot gas convection welding	5
4.5.4 Linear vibration welding	5
4.5.5 Orbital vibration welding	5
4.5.6 Spin welding	5
4.5.7 Laser welding	6
4.5.8 Hot plate welding	7
4.5.9 Heat staking – hot air	7
4.5.10 Heat staking – electrical	7
4.5.11 Heat staking – infrared	7
Annex A (informative) Template for TJPS: Ultrasonic welding/staking/spot welding	9
Annex B (informative) Template for TJPS: Infrared welding	11
Annex C (informative) Template for TJPS: Hot gas convection welding	13
Annex D (informative) Template for TJPS: Linear vibration welding	15
Annex E (informative) Template for TJPS: Orbital vibration welding	17
Annex F (informative) Template for TJPS: Spin welding	19
Annex G (informative) Template for TJPS: Laser welding	21
Annex H (informative) Template for TJPS: Hot plate welding	23
Annex I (informative) Template for TJPS: Heat staking – hot air	25
Annex J (informative) Template for TJPS: Heat staking – electrical	27
Annex K (informative) Template for TJPS: Heat staking – infrared	29
Annex L (informative) Worked example for TJPS: Hot plate welding	30
Annex M (informative) Worked example for TJPS: Heat staking – electrical	33
Bibliography	37

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document has been developed to help organizations better understand and implement controls with thermal joining processes through the use of thermal joining process specifications.

STANDARDSISO.COM : Click to view the full PDF of ISO 23512:2021

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 23512:2021

Plastics — Joining of thermoplastic moulded components — Specification of variables for thermal joining processes

1 Scope

This document specifies the minimum essential variables in order to produce a component of the required consistency and quality for the following thermal joining processes:

- ultrasonic welding/staking/spot welding;
- infrared welding;
- hot gas convection welding;
- linear vibration welding;
- orbital vibration welding;
- spin welding;
- laser welding;
- hot plate welding;
- heat staking: hot air;
- heat staking: electrical; and
- heat staking: infrared (IR).

This document defines the thermal joining process specification (TJPS) for each of the thermal joining processes listed above, to ensure that all the essential variables are properly considered, including the qualified range of each variable, in order to establish and maintain component quality at an acceptable level.

NOTE Standards on joining of plastic pipes, fittings, valves and/or auxiliary equipment, and the assessment of the properties of the resulting joints are developed and maintained by ISO/TC 138.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1
dimensional report

full measurement report on product before welding including flatness at weld joint

3.2
essential variable

joining condition that influences the quality of the joint and requires qualification

3.3
joining organization

organization responsible for the serial production joining and maintenance of quality

3.4
joining procedure

specified course of action to be followed in making a joint, including the *joining process(es)* (3.5), reference to materials, preparation, pre-heating (if necessary), control of process parameters and necessary equipment to be used

3.5
joining process

method of softening or melting to obtain a permanent *joint* (3.7)

3.6
joining process qualification record
JPQR

record comprising all data of mechanical test results for the specified range of each *essential variable* (3.2) needed for qualification of a TJPS, used by the *joining organization* (3.3) as part of the sign-off documentation

3.7
joint

junction of two sub-components

3.8
moisture content

amount of moisture content in parent material at the time of *welding* (3.12)

3.9
process report

document confirming that the sub-component has been manufactured using the correct moulding process parameters, conditions, material grade, masterbatch reference, masterbatch percentage, and regrind percentage

3.10
thermal joining process specification
TJPS

document that has been qualified and provides the required variables of the *joining procedure* (3.4) to ensure repeatability during production

3.11
visual examination acceptance criteria document

document specifying imperfections on sub-components that affect the functionality of the joint, such as weld lines, burn marks, surface contamination

3.12
welding

process of uniting softened surfaces of materials, generally with the aid of heat

3.13
work instruction

simplified TJPS, suitable for *joining process* (3.5) owner

4 Technical content of thermal joining process specification (TJPS)

4.1 General

A TJPS shall provide the minimum information specified in 4.2 to 4.5 required to make a joint of acceptable quality, as part of the component manufacturing quality agreement between the joining organization and the customer.

TJPSs cover a certain range for each essential variable. The range of each essential variable shall be qualified using a JPQR, and the procedure for measuring each variable shall conform to agreed specifications.

When completing the TJPS the technical support/manual/documentation of the joining process equipment manufacturer or service supplier may be consulted.

NOTE 1 Example templates of TJPSs are given in Annex A to Annex K. Worked example TJPSs for hot plate welding and heat staking: electrical are given in Annex L and Annex M, respectively.

NOTE 2 A work instruction can be prepared for each specific, applicable TJPS as part of detailed production planning.

4.2 Related to the joining organization

- a) identification of the joining organization;
- b) TJPS reference number/revision;
- c) signature of the person responsible for approval, appointed by the joining organization.

NOTE The responsibilities, knowledge, skills and competence for the person responsible for approval are set out in PD CEN/TR 16862^[1].

4.3 Related to the sub-component(s)

- a) sub-component material:
 - 1) material supplier name;
 - 2) designation of the material(s) and reference standard(s), if any, or an alternative identification if a reference standard does not exist;
 - 3) moisture content;
 - 4) regrind percentage;
 - 5) masterbatch reference and masterbatch percentage;
- b) dimensional report;
- c) process report;
- d) customer component/part number;
- e) supplier component/part number;
- f) visual examination acceptance criteria document number.

4.4 Common to all joining processes

- a) joint preparation;
- b) ambient temperature;

- c) sub-component temperature;
- d) joining process qualification record (JPQR).

4.5 Specific to a joining process

4.5.1 Ultrasonic welding/staking/spot welding

- a) joining process(es): welding, staking or spot welding;
- b) machine type (fixed or handheld);
- c) frequency;
- d) power rating;
- e) maximum tool temperature;
- f) tool face amplitude/amplitude profile;
- g) down speed;
- h) trigger force (if applicable)/(not handheld);
- i) pre-trigger/touch (yes/no) (not handheld);
- j) pre-trigger amplitude (if applicable)/(not handheld);
- k) joining force/force profile (if applicable)/(not handheld);
- l) meltdown/collapse/weld displacement (if applicable)/(not handheld);
- m) joining or welding time;
- n) hold/cooling time;
- o) weld energy.

NOTE A template for the TJPS for ultrasonic welding/staking/spot welding is given in [Annex A](#).

4.5.2 Infrared welding

- a) emitter condition;
- b) distance of sub-components from IR source;
- c) pre-heat/soak temperature (or power);
- d) pre-heat/soak time;
- e) full heat temperature/power;
- f) full heat time;
- g) removal of heating to sub-component contact time/changeover time;
- h) welding force;
- i) meltdown/collapse/weld displacement;
- j) cooling time.

NOTE A template for the TJPS for infrared welding is given in [Annex B](#).

4.5.3 Hot gas convection welding

- a) gas flow rate;
- b) gas temperature;
- c) gas feed type;
- d) distance between sub-components and tool;
- e) heating time;
- f) removal of heating to sub-component contact time/changeover time;
- g) welding force;
- h) meltdown/collapse/weld displacement;
- i) cooling time.

NOTE A template for the TJPS for hot gas convection welding is given in [Annex C](#).

4.5.4 Linear vibration welding

- a) frequency;
- b) amplitude/amplitude profile;
- c) IR pre-heat time (if applicable);
- d) IR pre-heat power (if applicable);
- e) IR pre-heat changeover time (if applicable);
- f) welding force/force profile;
- g) meltdown/collapse/weld displacement;
- h) welding time;
- i) hold/cooling time.

NOTE A template for the TJPS for linear vibration welding is given in [Annex D](#).

4.5.5 Orbital vibration welding

- a) frequency;
- b) amplitude/amplitude profile;
- c) welding force/force profile;
- d) meltdown/collapse/weld displacement;
- e) welding time;
- f) hold/cooling time.

NOTE A template for the TJPS for orbital vibration welding is given in [Annex E](#).

4.5.6 Spin welding

- a) machine type (servo-drive/inertia);

- b) head mass (inertia machines only);
- c) run-up time (inertia machines only);
- d) rotational speed;
- e) down speed;
- f) welding force/force profile;
- g) welding time;
- h) number of rotations (if applicable);
- i) meltdown/collapse/weld displacement;
- j) hold/cooling time;
- k) final angular position (if applicable).

NOTE A template for the TJPS for spin welding is given in [Annex F](#).

4.5.7 Laser welding

- a) wavelength;
- b) laser power;
- c) peak power (pulse lasers only);
- d) pulse energy (pulse lasers only);
- e) pulse duration and repetition rate (pulse lasers only);
- f) beam delivery (contour);
- g) focal length of focusing lens;
- h) beam energy profile/dimensions;
- i) power density;
- j) laser transmission of lower sub-component;
- k) laser transmission of upper sub-component;
- l) laser absorber type (if applicable);
- m) welding/clamping force;
- n) scan speed (if applicable);
- o) number of passes (if applicable);
- p) weld time (if applicable);
- q) meltdown/collapse/weld displacement;
- r) temperature close/loop (if applicable);
- s) power mapping/zoning (if applicable);
- t) hold/cooling time.

NOTE A template for the TJPS for laser welding is given in [Annex G](#).

4.5.8 Hot plate welding

- a) plate temperature;
- b) hot plate surface coating (if applicable);
- c) melting force;
- d) heating time;
- e) meltdown/collapse/displacement;
- f) removal of heating to part contact time/changeover time;
- g) welding force;
- h) weld collapse/displacement;
- i) hold/cooling time.

NOTE A template for the TJPS for hot plate welding is given in [Annex H](#).

4.5.9 Heat staking – hot air

- a) hot air temperature;
- b) airflow;
- c) distance of stake pin from end of nozzle;
- d) heating time;
- e) changeover time;
- f) cold stake tool/platen force;
- g) cold stake tool contact time;
- h) final cold tool position/dead stop (if applicable).

NOTE A template for the TJPS for heat staking – hot air is given in [Annex I](#).

4.5.10 Heat staking – electrical

- a) heated tool temperature/temperature profile;
- b) heating time (if no temperature profile);
- c) tool/platen force;
- d) cooling time (if no temperature profile);
- e) release temperature (if no temperature profile);
- f) final tool position/dead stop (if applicable).

NOTE A template for the TJPS for heat staking – electrical is given in [Annex J](#).

4.5.11 Heat staking – infrared

- a) IR power;
- b) distance of stake pin from heat source;

- c) heating time;
- d) cold stake tool/platen force;
- e) cold stake tool contact time.

NOTE A template for the TJPS for heat staking - infrared is given in [Annex K](#).

STANDARDSISO.COM : Click to view the full PDF of ISO 23512:2021

Annex A (informative)

Template for TJPS: Ultrasonic welding/staking/spot welding

Thermal joining process specification (TJPS): Ultrasonic welding/staking/spot welding			
Joining organization:		TJPS reference number/revision:	
Component name:			
Customer component/ part number		Supplier component/ part number	
JPQR number:			

Sub-component A*:		Sub-component B:	
Material type/designation:		Material type/designation:	
Material supplier name		Material supplier name	
Material grade		Material grade	
Masterbatch reference		Masterbatch reference	
Masterbatch percentage		Masterbatch percentage	
Regrind (%)		Regrind (%)	
Moisture content range (%)		Moisture content range (%)	
Dimensional report number		Dimensional report number	
Process report number		Process report number	
Visual examination acceptance criteria document number		Visual examination acceptance criteria document number	

* Sub-component A is the part in initial contact with the sonotrode/horn

Joining process (welding/staking/spot welding):

Machine characteristics
Machine type (fixed/handheld):
Frequency (kHz):
Power rating (kW):

Joining parameters	Value/tolerance or range
Ambient temperature (°C)	
Sub-component temperature (°C)	
Tool temperature (°C)	
Tool face amplitude (µm) / amplitude profile	
Down speed (mm/s) (not handheld)	
Trigger force (N) (if applicable) (not handheld)	
Pre-trigger / touch (yes/no) (not handheld)	
Pre-trigger amplitude (µm) (if applicable) (not handheld)	
Joining force (N) / force profile (not handheld)	
Meltdown / collapse / weld displacement (mm) (not handheld)	
Joining or welding time (s)	
Hold / cooling time (s)	
Weld energy (J)	

Compiled by:	Signature:
	Date:
Approved by:	Signature:
	Date:

Joint design

Provide the figure(s) of your joint design here.

Amplitude profile diagram (if applicable)

Provide diagram, if applicable.

Force profile diagram (if applicable)

Provide diagram, if applicable.

Annex B (informative)

Template for TJPS: Infrared welding

Thermal joining process specification (TJPS): Infrared welding			
Joining organization:		TJPS reference number/revision:	
Component name:			
Customer component/ part number		Supplier component/ part number	
JPQR number:			

Sub-component A:		Sub-component B:	
Material type/designation:		Material type/designation:	
Material supplier name		Material supplier name	
Material grade		Material grade	
Masterbatch reference		Masterbatch reference	
Masterbatch percentage		Masterbatch percentage	
Regrind (%)		Regrind (%)	
Moisture content range (%)		Moisture content range (%)	
Dimensional report number		Dimensional report number	
Process report number		Process report number	
Visual examination acceptance criteria document number		Visual examination acceptance criteria document number	

Machine characteristics
Machine identification:
Emitter type:

Joining parameters	Value/tolerance or range
Ambient temperature (°C)	
Sub-component temperature (°C)	
Emitter condition	
Distance of sub-components from IR source (mm)	
Pre-heat/soak temperature (°C) / power (%)	
Pre-heat/soak time (s)	
Full heat temperature (°C) / power (%)	
Full heat time (s)	
Removal of heating to sub-component contact time / change-over time (s)	
Welding force (N)	
Meltdown / collapse / weld displacement (mm)	
Cooling time (s)	

Compiled by:	Signature: Date:
Approved by:	Signature: Date:

Joint design

Provide the figure(s) of your joint design here.

STANDARDSISO.COM : Click to view the full PDF of ISO 23512:2021

Annex C

(informative)

Template for TJPS: Hot gas convection welding

Thermal joining process specification (TJPS): Hot gas convection welding			
Joining organization:		TJPS reference number/revision:	
Component name:			
Customer component/ part number		Supplier component/ part number	
JPQR number:			

Sub-component A:		Sub-component B:	
Material type/designation:		Material type/designation:	
Material supplier name		Material supplier name	
Material grade		Material grade	
Masterbatch reference		Masterbatch reference	
Masterbatch percentage		Masterbatch percentage	
Regrind (%)		Regrind (%)	
Moisture content range (%)		Moisture content range (%)	
Dimensional report number		Dimensional report number	
Process report number		Process report number	
Visual examination acceptance criteria document number		Visual examination acceptance criteria document number	

Machine characteristics
Machine identification:

Joining parameters	Value/tolerance or range
Ambient temperature (°C)	
Sub-component temperature (°C)	
Gas temperature (°C)	
Gas flow rate (standard litres per minute)	
Gas feed type	
Distance between sub-components and tool (mm)	
Heating time (s)	
Removal of heating to sub-component contact time / changeover time (s)	
Welding force (N)	
Meltdown / collapse / weld displacement (mm)	
Cooling time (s)	

Compiled by:	Signature: Date:
Approved by:	Signature: Date:

Joint design

Provide the figure(s) of your joint design here.

STANDARDSISO.COM : Click to view the full PDF of ISO 23512:2021

Annex D (informative)

Template for TJPS: Linear vibration welding

Thermal joining process specification (TJPS): Linear vibration welding			
Joining organization:		TJPS reference number/revision:	
Component name:			
Customer component/ part number		Supplier component/ part number	
JPQR number:			

Sub-component A:		Sub-component B:	
Material type/designation:		Material type/designation:	
Material supplier name		Material supplier name	
Material grade		Material grade	
Masterbatch reference		Masterbatch reference	
Masterbatch percentage		Masterbatch percentage	
Regrind (%)		Regrind (%)	
Moisture content range (%)		Moisture content range (%)	
Dimensional report number		Dimensional report number	
Process report number		Process report number	
Visual examination acceptance criteria document number		Visual examination acceptance criteria document number	

Joining parameters	Value/tolerance or range
Ambient temperature (°C)	
Sub-component temperature (°C)	
Frequency (Hz)	
Amplitude (mm) / amplitude profile	
IR pre-heat time (s) (if applicable)	
IR pre-heat power (%) (if applicable)	
IR pre-heat changeover time (s) (if applicable)	
Welding force (N) / force profile	
Meltdown / collapse / weld displacement (mm)	
Welding time (s)	
Hold/cooling time (s)	

Compiled by:	Signature:
	Date:
Approved by:	Signature:
	Date:

Joint design

Provide the figure(s) of your joint design here.

Amplitude profile diagram (if applicable)

Provide diagram, if applicable.

Force profile diagram (if applicable)

Provide diagram, if applicable.

STANDARDSISO.COM : Click to view the full PDF of ISO 23512:2021

Annex E (informative)

Template for TJPS: Orbital vibration welding

Thermal joining process specification (TJPS): Orbital vibration welding			
Joining organization:		TJPS reference number/revision:	
Component name:			
Customer component/ part number		Supplier component/ part number	
JPQR number:			

Sub-component A:		Sub-component B:	
Material type/designation:		Material type/designation:	
Material supplier name		Material supplier name	
Material grade		Material grade	
Masterbatch reference		Masterbatch reference	
Masterbatch percentage		Masterbatch percentage	
Regrind (%)		Regrind (%)	
Moisture content range (%)		Moisture content range (%)	
Dimensional report number		Dimensional report number	
Process report number		Process report number	
Visual examination acceptance criteria document number		Visual examination acceptance criteria document number	

Joining parameters	Value/tolerance or range
Ambient temperature (°C)	
Sub-component temperature (°C)	
Frequency (Hz)	
Amplitude (mm) / amplitude profile	
Welding force (N) / force profile	
Meltdown / collapse / weld displacement (mm)	
Welding time (s)	
Hold/cooling time (s)	

Compiled by:	Signature:
	Date:
Approved by:	Signature:
	Date:

Joint design

Provide the figure(s) of your joint design here.

Amplitude profile diagram (if applicable)

Provide diagram, if applicable.

Force profile diagram (if applicable)

Provide diagram, if applicable.

STANDARDSISO.COM : Click to view the full PDF of ISO 23512:2021

Annex F (informative)

Template for TJPS: Spin welding

Thermal joining process specification (TJPS): Spin welding			
Joining organization:		TJPS reference number/revision:	
Component name:			
Customer component/ part number		Supplier component/ part number	
JPQR number:			

Sub-component A:		Sub-component B:	
Material type/designation:		Material type/designation:	
Material supplier name		Material supplier name	
Material grade		Material grade	
Masterbatch reference		Masterbatch reference	
Masterbatch percentage		Masterbatch percentage	
Regrind (%)		Regrind (%)	
Moisture content range (%)		Moisture content range (%)	
Dimensional report number		Dimensional report number	
Process report number		Process report number	
Visual examination acceptance criteria document number		Visual examination acceptance criteria document number	

Machine characteristics
Machine type (servo drive / inertia):

Joining parameters	Value/tolerance or range
Ambient temperature (°C)	
Sub-component temperature (°C)	
Head mass (kg) (inertia machines only)	
Run-up time (s) (inertia machines only)	
Rotational speed (rpm)	
Down speed (mm/s)	
Welding force (N) / force profile	
Welding time (s)	
Number of rotations (if applicable)	
Meltdown / collapse / weld displacement (mm)	
Hold/cooling time (s)	
Final angular position (°) (if applicable)	

Compiled by:	Signature:
	Date:
Approved by:	Signature:
	Date:

Joint design

Provide the figure(s) of your joint design here.

Force profile diagram (if applicable)

Provide diagram, if applicable.

STANDARDSISO.COM : Click to view the full PDF of ISO 23512:2021

Annex G (informative)

Template for TJPS: Laser welding

Thermal joining process specification (TJPS): Laser welding			
Joining organization:		TJPS reference number/revision:	
Component name:			
Customer component/ part number		Supplier component/ part number	
JPQR number:			

Sub-component A:		Sub-component B:	
Material type/designation:		Material type/designation:	
Material supplier name		Material supplier name	
Material grade		Material grade	
Masterbatch reference		Masterbatch reference	
Masterbatch percentage		Masterbatch percentage	
Regrind (%)		Regrind (%)	
Moisture content range (%)		Moisture content range (%)	
Laser transmission (%)		Laser transmission (%)	
Dimensional report number		Dimensional report number	
Process report number		Process report number	
Visual examination acceptance criteria document number		Visual examination acceptance criteria document number	

Joint preparation
Laser absorber type (if applicable):

Machine characteristics
Machine type (fixed / handheld):
Wavelength (μm)
Beam manipulation system (contour / quasi-simultaneous / simultaneous / mask)
Beam energy profile/dimensions (e.g. wave guide, Gaussian, flat top or line)
Focal length of focusing lens (mm) (if applicable)

Joining parameters	Value/tolerance or range
Ambient temperature (°C)	
Sub-component temperature (°C)	
Laser power (W)	
Peak power (W) (pulse lasers only)	
Pulse energy (J) (pulse lasers only)	
Pulse duration (ms) and repetition rate (Hz) (pulse lasers only)	
Power density (W/mm ²)	
Welding / clamping force (N)	
Scan speed (mm/s) (if applicable)	
Number of passes (if applicable)	
Weld time (s) (if applicable)	
Meltdown / collapse / weld displacement (mm)	
Temperature close/loop (°C) (if applicable)	
Power mapping/zoning (if applicable)	
Hold/cooling time (s)	

Compiled by:	Signature:
	Date:
Approved by:	Signature:
	Date:

Joint design

Provide the figure(s) of your joint design here.

Power zone mapping (if applicable)

Provide diagram, if applicable.

Annex H (informative)

Template for TJPS: Hot plate welding

Thermal joining process specification (TJPS): Hot plate welding			
Joining organization:		TJPS reference number/revision:	
Component name:			
Customer component/ part number		Supplier component/ part number	
JPQR number:			

Sub-component A:		Sub-component B:	
Material type/designation:		Material type/designation:	
Material supplier name		Material supplier name	
Material grade		Material grade	
Masterbatch reference		Masterbatch reference	
Masterbatch percentage		Masterbatch percentage	
Regrind (%)		Regrind (%)	
Moisture content range (%)		Moisture content range (%)	
Dimensional report number		Dimensional report number	
Process report number		Process report number	
Visual examination acceptance criteria document number		Visual examination acceptance criteria document number	

Machine characteristics
Hot plate / tool surface coating:

Joining parameters	Value/tolerance or range
Ambient temperature (°C)	
Sub-component temperature (°C)	
Plate temperature (°C)	
Melting force (N)	
Heating time (s)	
Meltdown / collapse / displacement (mm)	
Removal of heating to sub-component contact time / changeover time (s)	
Welding force (N)	
Weld collapse/displacement (mm)	
Hold/cooling time (s)	

Compiled by:	Signature: Date:
Approved by:	Signature: Date:

Note a worked example of a TJPS for hot plate welding is given in [Annex L](#).

Joint design

Provide the figure(s) of your joint design here.

STANDARDSISO.COM : Click to view the full PDF of ISO 23512:2021

Annex I (informative)

Template for TJPS: Heat staking – hot air

Thermal joining process specification (TJPS): Heat staking – hot air			
Joining organization:		TJPS reference number/revision:	
Component name:			
Customer component/ part number		Supplier component/ part number	
JPQR number:			

Sub-component A*:		Sub-component B:	
Material type/designation:		Material type/designation:	
Material supplier name		Material supplier name	
Material grade		Material grade	
Masterbatch reference			
Masterbatch percentage			
Regrind (%)			
Moisture content range (%)		Moisture content range (%)	
Dimensional report number		Dimensional report number	
Process report number		Process report number	
Visual examination acceptance criteria document number		Visual examination acceptance criteria document number	

* Sub-component A is the formed part in staking

Joining parameters	Value/tolerance or range
Ambient temperature (°C)	
Sub-component temperature (°C)	
Hot air temperature (°C)	
Air flow (m/s or standard litres per minute)	
Distance of stake pin from end of nozzle (mm)	
Heating time (s)	
Changeover time (s)	
Cold stake tool/platen force (N)	
Cold stake tool contact time (s)	
Final cold tool position / dead stop (mm) (if applicable)	

Compiled by:	Signature: Date:
Approved by:	Signature: Date:

Joint design

Provide the figure(s) of your joint design here.

STANDARDSISO.COM : Click to view the full PDF of ISO 23512:2021

Annex J (informative)

Template for TJPS: Heat staking – electrical

Thermal joining process specification (TJPS): Heat staking – electrical			
Joining organization:		TJPS reference number/revision:	
Component name:			
Customer component/ part number		Supplier component/ part number	
JPQR number:			

Sub-component A*:		Sub-component B:	
Material type/designation:		Material type/designation:	
Material supplier name		Material supplier name	
Material grade		Material grade	
Masterbatch reference			
Masterbatch percentage			
Regrind (%)			
Moisture content range (%)		Moisture content range (%)	
Dimensional report number		Dimensional report number	
Process report number		Process report number	
Visual examination acceptance criteria document number		Visual examination acceptance criteria document number	

* Sub-component A is the formed part in staking

Joining parameters	Value/tolerance or range
Ambient temperature (°C)	
Sub-component temperature (°C)	
Heated tool temperature (°C) / temperature profile	
Heating time (s) (if no temperature profile)	
Tool/platen force (N)	
Cooling time (s) (if no temperature profile)	
Release temperature (°C) (if no temperature profile)	
Final cold tool position / dead stop (mm) (if applicable)	

Compiled by:	Signature: Date:
Approved by:	Signature: Date:

Note a worked example of a TJPS for heat staking – electrical is given in [Annex M](#)

Joint design

Provide the figure(s) of your joint design here.

Temperature profile (if applicable)

Provide diagram, if applicable.

STANDARDSISO.COM : Click to view the full PDF of ISO 23512:2021

Annex K (informative)

Template for TJPS: Heat staking – infrared

Thermal joining process specification (TJPS): Heat staking – infrared			
Joining organization:		TJPS reference number/revision:	
Component name:			
Customer component/ part number		Supplier component/ part number	
JPQR number:			

Sub-component A*:		Sub-component B:	
Material type/designation:		Material type/designation:	
Material supplier name		Material supplier name	
Material grade		Material grade	
Masterbatch reference			
Masterbatch percentage			
Regrind (%)			
Moisture content range (%)		Moisture content range (%)	
Dimensional report number		Dimensional report number	
Process report number		Process report number	
Visual examination acceptance criteria document number		Visual examination acceptance criteria document number	

* Sub-component A is the formed part in staking

Joining parameters	Value/tolerance or range
Ambient temperature (°C)	
Sub-component temperature (°C)	
IR power (W)	
Distance of stake pin from heat source (mm)	
Heating time (s)	
Cold stake tool/platen force (N)	
Cold stake tool contact time (s)	

Compiled by:	Signature:
	Date:
Approved by:	Signature:
	Date:

Joint design

Provide the figure(s) of your joint design here.