INTERNATIONAL STANDARD

ISO 2795

Sixth edition 2020-06

Plain bearings — Sintered bushes — Dimensions and tolerances

Paliers lisses — Coussinets frittés — Dimensions et tolérances dimensions et de la consecution dimension et de la consecution et de la consecution et de la consecution et

ISO

STANDARDS 150 COM. Click to view the full Policy of 150 2705 2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org

Website: www.iso.org Published in Switzerland

Co	ntents		Page
For	eword		iv
Intr	oduction		v
1	Scope		1
2	Normative references		1
3	Terms and definitions		1
4	Material		1
5	5.1 Dimensions		1
6	Flanged bearings 6.1 Dimensions 6.2 Tolerances		4
7	Spherical bearing		8 9
	STANDARDSISO.COM. Click	to view the	

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee SC 7, Special types of plain bearings.

This sixth edition cancels and replaces the fifth edition (ISO 2795:2014), of which it constitutes a minor revision.

The main changes compared to the previous edition are as follows:

- Clause 3 has been added:
- all figures have been reviewed
- titles of figures and tables have been added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The sizes given in this document are based on a range of shaft diameters which are considered to correspond to the requirements of industry. For all except the smallest sizes, a thin-wall series is provided in addition to the normal series in order to introduce an element of choice and, more importantly, to provide for the possibility of the same sizes being adopted for plain bearings made from other materials.

It is envisaged that as far as possible, the same outside diameters will be recommended for all types of plain bearings.

ed f

STANDARDS GO.COM. Clickto view the full Political STANDARDS GO.COM.

STANDARDS 50.COM. Cick to view the full Part of 150 2 Tost 2020

Plain bearings — Sintered bushes — Dimensions and tolerances

1 Scope

This document specifies the dimensions and tolerances applicable to sintered bearings for the following ranges of inside diameters:

- cylindrical bearings: 1 mm to 60 mm;
- flanged bearings: 1 mm to 60 mm;
- spherical bearings: 1 mm to 20 mm.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5755, Sintered metal materials — Specifications

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform available at https://www.iso.org/obp
- IEC Electropedia: available at http://www.electropedia.org/

4 Material

Materials used for manufacturing sintered bearings shall conform to ISO 5755.

5 Cylindrical bearings

5.1 Dimensions

Dimensions for cylindrical bearings are shown in Figure 1, Table 1 and Table 2.




Table 1 — Preferred nominal dimensions for cylindrical bearings

	Inside diameter	Outside o		Length
	d	Normal series	Thin-wall series ^a	L
	1	B.	_	1-2
	1,5	4	_	1–2
	2	5	_	2-3
	2,5	6	_	2-3
	3	6	5	3-4
	4	8	7	3-4-6
	5	9	8	4-5-8
	6	10	9	4-6-10
C.	7	11	10	5-8-10
	8	12	11	6-8-12
	9	14	12	6-10-14
	10	16	14	8-10-16
	12	18	16	8-12-20
	14	20	18	10-14-20
	15	21	19	10-15-25
	16	22	20	12-16-25
	18	24	22	12-18-30

For inside diameter 20 mm (included), the last value for the length is not applicable to the thin-wall series.

Dimensions in parentheses shall be used as "second choice".

Table 1 (continued)

Inside diameter	Outside o	_	Length
d	Normal series	Thin-wall seriesa	L
20	26	25	15-20-25-30
22	28	27	15-20-25-30
25	32	30	20-25-30-35
28	36	33 (34) ^b	20-25-30-40
30	38	35 (36) ^b	20-25-30-40
32	40	38	20-25-30-40
35	45	41	25-35-40-50
38	48	44	25-35-45-55
40	50	46	30-40-50-60
42	52	48	30-40-50-60
45	55	51	35-45-55-65
48	58	55	35-50-70
50	60	58	35-50-70
55	65	63	40-55-70
60	72	68	50-60-70

For inside diameter 20 mm (included), the last value for the length is not applicable to the thin-wall series.

Table 2 — Chamfers

Dimensions in millimetres

	Wall thickness D-d		Chamfer <i>C</i>
	above	up to and incl.	max.
	C	1	0,2
	1	2	0,3
	2	3	0,4
7	3	4	0,6
	4	5	0,7
	5	_	0,8

5.2 Tolerances

The tolerances for the bearings after fitting and the tolerances for the housing and insertion pin are given below. In addition, the tolerances for the inside and outside diameters of the bearings before fitting are given.

Since the actual tolerances and combinations of tolerances in the as-delivered state depend upon the characteristics of the materials and the manufacturing methods, they should be discussed with the manufacturer.

Dimensions in parentheses shall be used as "second choice".

ISO 2795:2020(E)

As-delivered:

- on outside diameter, D: in the ranges
 - r6 to s7, for $D \le 50$ mm, and
 - r7 to s8, for D > 50 mm;
- on inside diameter, *d*: in the ranges
 - F7 to G7, for $D \le 50$ mm, of and
 - F8 to G8, for D > 50 mm;
- on bearing length, L: js13;
- on bearing length, L: JS13;

 on coaxiality of the outside diameter with respect to the inside surface diameter (tolerance based on the outside diameter, D)

 t1 = IT9, for $D \le 50$ mm, and

 t2 = IT10, for D > 50 mm.

 ertion pin: in the range m5 to m6.

 using: H7.

 aring bore after fitting (assuming the housing is rigid):

 H7, for $D \le 50$ mm;

 H8, for D > 50 mm.

 Flanged bearings

 Dimensions

 nensions for flanged bearings are Slown in Figure 2, Table 3, Table 4 and Table 5.

Insertion pin: in the range m5 to m6.

Housing: H7.

Bearing bore after fitting (assuming the housing is rigid):

6.1 Dimensions

Dimensions for flanged bearings are shown in Figure 2, Table 3, Table 4 and Table 5.




Figure 2 — Flanged bearing

Table 3 — Preferred nominal dimensions for flanged bearings

Inside	Outside	Flange	Flange	Length	
d	D	$D_{\rm fl}$	e	L	
Normal series					
1	3	5	1	2	
1,5	4	6	1	2	
2,6	5	8	1,5	3	
2,5	6	9	1,5	3	
2 3	6	9	1,5	4	
4	8	12	2	3-4-6	
5	9	13	2	4-5-8	
6	10	14	2	4-6-10	
7	11	15	2	5-8-10	
8	12	16	2	6-8-12	
9	14	19	2,5	6-10-14	
10	16	22	3	8-10-16	
12	18	24	3	8-12-20	
14	20	26	3	10-14-20	
15	21	27	3	10-15-25	
16	22	28	3	12-16-25	
18	24	30	3	12-18-30	
20	26	32	3	15-20-25-30	
22	28	34	3	15-20-25-30	
	1 1,5 2,5 3 4 5 6 7 8 9 10 12 14 15 16 18 20	diameter diameter 1 3 1,5 4 2 5 25 6 3 6 4 8 5 9 6 10 7 11 8 12 9 14 10 16 12 18 14 20 15 21 16 22 18 24 20 26	$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	

 Table 3 (continued)

Inside diameter d	Outside diameter D	Flange diameter D_{fl}	Flange thickness e	Length <i>L</i>
25	32	39	3,5	20-25-30
28	36	44	4	20-25-30
30	38	46	4	20-25-30
32	40	48	4	20-25-30
35	45	55	5	25-35-40
38	48	58	5	25-35-45
40	50	60	5	30-40-50
42	52	62	5	30-40-50
45	55	65	5	35-45-55
48	58	68	5	35-50
50	60	70	5	35-50
55	65	75	5	40-55
60	72	84	6	50-60
Thin-wall series				
10	14	18	2	8-10-16
12	16	20	2 ()	8-12-20
14	18	22	*//&	10-14-20
15	19	23	<i>N</i> 2	10-15-25
16	20	24	2	12-16-25
18	22	26.0	2	12-18-30
20	25	. 30	2,5	15-20-25
22	27	32	2,5	15-20-25
25	30	• 35	2,5	20-25-30
Table 4 — Chamfers Dimensions in millimetres				

	/	
Walthickness $\frac{D-d}{2}$		Chamfer <i>C</i>
above	up to and incl.	max.
_	1	0,2
1	2	0,3
2	3	0,4
3	4	0,6
4	5	0,7
5	_	0,8

Table 5 — Flange radii

Outside diameter D		r
above	up to and incl.	max.
_	12	0,3
12	30	0,6
30	_	0,8

6.2 Tolerances

The tolerances for the bearings after fitting and the tolerances for the housing and insertion pin are given below. In addition, the tolerances for the inside and outside diameters of the bearing and on the flange before fitting are given.

Since the actual tolerances and combinations of tolerances in the as-delivered state depend upon the characteristics of the materials and the manufacturing methods, they should be discussed with the manufacturer.

As-delivered:

- on outside diameter, *D*: in the ranges
 - r6 to s7, for $D \le 50$ mm, and
 - r7 to s8, for D > 50 mm;
- on inside diameter, *d*: in the ranges
 - F7 to G7, for $D \le 50$ mm, and
 - F8 to G8, for D > 50 mm;
- on bearing length, *L*: js13
- on flange diameter, D₁: js13;
- on flange thickness, e: js13;
- on coaxiality of the outside diameter with respect to the inside surface diameter (tolerance based on the outside diameter, D)
 - t1 = 179, for $D \le 50$ mm, and
 - t2 = IT10, for D > 50 mm.

Insertion pin: in the range m5 to m6.

Housing: H7.


Bearing bore after fitting (assuming the housing is rigid):

- H7, for $D \le 50$ mm;
- H8, for D > 50 mm.

Spherical bearing

Dimensions

Dimensions for spherical bearings are shown in Figure 3 and Table 6.



A cylindrical surface is permissible on the sphere at the centre of the bearing length, the diameter of which should be agreed upon by the user and the manufacturer.

Table 6 — Preferred nominal dimensions for spherical bearings

Dimensions in millimetres Inside **Spherical** Chamfer Length diameter diameter \mathcal{C} L D_{S} max. 3 2 3 1,5 4,5 2 5 3 0,3 2,5 6 4 8 3 6 4 10 8