
Reclaimed isobutene-isoprene (IIR) rubber — Evaluation procedure

*Caoutchouc isobutène-isoprène (IIR) régénéré — Méthode
d'évaluation*

STANDARDSISO.COM : Click to view the full PDF of ISO/TS 16096:2021



STANDARDSISO.COM : Click to view the full PDF of ISO/TS 16096:2021



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Sampling and sample preparation	2
5 Physical and chemical tests on raw rubber	2
5.1 Mooney viscosity	2
5.2 Acetone extract	2
5.3 Ash	2
5.4 Carbon black	2
5.5 Rubber content	2
6 Preparation of test mix for evaluation	2
6.1 Standard test formulation	2
6.2 Mixing procedure — Mixing with a laboratory mill	3
7 Evaluation of vulcanization characteristics by a curemeter test	4
7.1 Using an oscillating disc curemeter	4
7.2 Using a rotorless curemeter	4
8 Evaluation of Mooney viscosity of test mixes	5
9 Evaluation of tensile stress-strain properties of vulcanized test mixes	5
10 Evaluation of Shore hardness of vulcanized test mixes	5
11 Test report	5
Bibliography	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This second edition cancels and replaces the first edition (ISO/TS 16096:2014), which has been technically revised.

The main changes compared to the previous edition are as follows:

- update of the normative references;
- addition of the CAS numbers in [Table 1](#);
- addition of a Bibliography.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Reclaimed isobutene-isoprene (IIR) rubber — Evaluation procedure

1 Scope

This document defines

- physical and chemical tests on raw reclaimed isobutene-isoprene (IIR) rubber, and
- standard materials, standard test formulations, equipment, and processing methods for evaluating the vulcanization characteristics and the mechanical properties of reclaimed isobutene-isoprene rubber.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 48-4, *Rubber, vulcanized or thermoplastic — Determination of hardness — Part 4: Indentation hardness by durometer method (Shore hardness)*

ISO 247-1:2018, *Rubber — Determination of ash — Part 1: Combustion method*

ISO 289-1, *Rubber, unvulcanized — Determinations using a shearing-disc viscometer — Part 1: Determination of Mooney viscosity*

ISO 1382, *Rubber — Vocabulary*

ISO 1407:2011, *Rubber — Determination of solvent extract*

ISO 1408:1995, *Rubber — Determination of carbon black content — Pyrolytic and chemical degradation methods*

ISO 1795, *Rubber, raw natural and raw synthetic — Sampling and further preparative procedures*

ISO 6502-2, *Rubber — Measurement of vulcanization characteristics using curemeters — Part 2: Oscillating disc curemeter*

ISO 6502-3, *Rubber — Measurement of vulcanization characteristics using curemeters — Part 3: Rotorless curemeter*

ASTM D297-15(2019), *Standard Test Methods for Rubber Products — Chemical Analysis*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1382 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Sampling and sample preparation

4.1 Take a laboratory sample of approximately 1,5 kg by the method described in ISO 1795.

4.2 Prepare the test sample in accordance with ISO 1795.

5 Physical and chemical tests on raw rubber

5.1 Mooney viscosity

Determine the Mooney viscosity in accordance with ISO 289-1 on a test sample prepared as indicated in [4.2](#).

Record the result as ML(1 + 4) at 100 °C.

5.2 Acetone extract

Determine the acetone extract in accordance with method A or method B of ISO 1407:2011.

5.3 Ash

Determine the ash content in accordance with method A of ISO 247-1:2018.

5.4 Carbon black

Determine the carbon black content in accordance with ISO 1408:1995, Method A.

5.5 Rubber content

Determine the rubber content, R (in %), in accordance with ASTM D297-15(2019), Clauses 11, 12, and 13.

$$R = 100 - (a + b + c) \quad (1)$$

where

a is the carbon black content, in percent (%);

b is the ash content, in percent (%);

c is the acetone extract, in percent (%).

6 Preparation of test mix for evaluation

6.1 Standard test formulation

The standard test formulation for evaluation of reclaimed isobutene-isoprene rubber is given in [Table 1](#).

The materials used shall be national or International standard reference materials. If no standard reference material is available, the materials to be used shall be agreed between the interested parties.

Table 1 — Standard test formulation

Material	CAS number	Parts by mass
Reclaimed isobutene-isoprene rubber (IIR)		100,00 + x + y + z
Zinc oxide ^a	1314-13-2	5,00
Sulfur ^a	7704-34-9	2,00
ZBEC (zinc dibenzylthiocarbamate) ^a	14726-36	1,50
Mercaptobenzothiazole (MBT)	149-30-4	1,00
NOTE 1 x is the number of parts of carbon black to 100 parts of rubber in reclaimed isobutene-isoprene rubber.		
NOTE 2 y is the number of parts of acetone extract to 100 parts of rubber in reclaimed isobutene-isoprene rubber.		
NOTE 3 z is the number of parts of ash to 100 parts of rubber in reclaimed isobutene-isoprene rubber.		
^a Powder materials are used (standard curing ingredients used in the industry).		

6.2 Mixing procedure — Mixing with a laboratory mill

The standard laboratory mill-batch mass, in grams, shall be enough to form proper rolling band. The surface temperature of the rolls shall be maintained at $50\text{ °C} \pm 5\text{ °C}$ throughout the mixing.

A good rolling bank at the nip of the rolls shall be maintained during mixing. If this is not obtained with the nip settings specified hereunder, small adjustments to the mill openings may be necessary.

A mill batch mass based on two times the formulation mass can also be used. However in this case, more adjustment to the mill openings is necessary.

	Duration min	Cumulative time min
a) Band the reclaimed rubber with the mill opening set at 1,2 mm.	1,0	1,0
b) Add the zinc oxide across the mill rolls at a uniform rate. When all the zinc oxide has been incorporated, make a 3/4 cut from each side.	1,0	2,0
Do not cut the batch while powder is evident in the bank or on the milling surface. Be certain to return to the batch any materials that drop through the mill.		
c) Add the MBT across the mill rolls at a uniform rate. When all the powder has been incorporated, make a 3/4 cut from each side.	1,0	3,0
d) Add the ZBEC across the mill rolls at a uniform rate. When all the powder has been incorporated, make a 3/4 cut from each side.	1,0	4,0
e) Add the sulfur across the mill rolls at a uniform rate. When all the sulfur has been incorporated, make a 3/4 cut from each side.	1,0	5,0
f) Cut the batch from the mill and take off the mill rolls.	2,0	7,0
g) Set the mill opening to 1,2 mm and pass the rolled batch endwise through the mill 12 times.	3,0	10,0
Total time (max.)	10,0	

h) Sheet the batch in grain direction to an approximate thickness of 6 mm and check-weigh the batch (see ISO 2393). If the mass of the batch differs from the theoretical value by more than +0,5 % or -1,5 %, discard the batch and re-mix.

i) Remove sufficient material for curemeter testing.

- l) Sheet the batch to approximately 2,2 mm for preparing test slabs or to the appropriate thickness for preparing ISO ring or dumbbell test pieces in accordance with ISO 37.
- j) After mixing, condition the batch for at least 2 h, but not more than 24 h, if possible at standard laboratory temperature and humidity as defined in ISO 23529.

NOTE For very low Mooney viscosity reclaim rubber, tendency of reclaim sticking to the roll can be observed. Hence, cutting as mentioned in the procedure is sometime not possible. In such case, scraper blade as shown in [Figure 1](#) can be used. After scraping the material each time, it needs to be folded two times and passed through mill again to ensure proper blending of chemical.



Key

- 1 scraper blade

Figure 1 — Example of scraper blade

7 Evaluation of vulcanization characteristics by a curemeter test

7.1 Using an oscillating disc curemeter

Measure the following standard test parameters:

M_L , M_H at defined time, t_{s1} , $t'_c(50)$, $t'_c(90)$, $t'_c(95)$, and $t'_c(99)$

in accordance with ISO 6502-2, using the following test conditions:

- oscillation frequency: 1,7 Hz (100 cycles per minute);
- amplitude of oscillation: 1° of arc (an amplitude of oscillation of 3° of arc is permitted as an alternative. If such an amplitude is chosen, measure t_{s2} instead of t_{s1});
- torque range: to be chosen to give at least 75 % of full-scale deflection at M_H ;
- die temperature: 160 °C ± 0,3 °C;
- pre-heat time: none.

7.2 Using a rotorless curemeter

Measure the following standard test parameters:

F_L, F_{\max} at defined time, $t_{s1}, t'_c(50), t'_c(90), t'_c(95)$ and $t'_c(99)$

in accordance with ISO 6502-3, using the following test conditions:

- oscillation frequency: 1,7 Hz (100 cycles per minute);
- amplitude of oscillation: 0,5° of arc (an amplitude of oscillation of 1° of arc is permitted as an alternative. If such an amplitude is chosen, measure t_{s2} instead of t_{s1});
- torque range: to be chosen to give at least 75 % of full-scale deflection at F_{\max} ;
- die temperature: 160 °C ± 0,3 °C;
- pre-heat time: none.

The two types of curemeter might not give identical results.

8 Evaluation of Mooney viscosity of test mixes

Determine the Mooney viscosity in accordance with ISO 289-1.

Record the result as ML(1 + 4) at 100 °C.

9 Evaluation of tensile stress-strain properties of vulcanized test mixes

WARNING — Formation of nitrosamines is possible during the cure.

Vulcanize sheets at 160 °C for 30 min.

Condition the vulcanized sheets/buttons for 16 h to 96 h at a standard laboratory temperature and, if possible, at a standard laboratory humidity as defined in ISO 23529.

Measure the stress-strain properties in accordance with ISO 37.

10 Evaluation of Shore hardness of vulcanized test mixes

Measure the Shore hardness using durometers with the A-scale for rubbers in the normal hardness range in accordance with ISO 48-4.

11 Test report

The test report shall include the following:

- a) a reference to this document (i.e. ISO/TS 16096:2021);
- b) all details necessary for the identification of the sample;
- c) the method used for the ash determination (method A of ISO 247-1:2018);
- d) the method used for the acetone extract determination (method A or method B of ISO 1407:2011);
- e) the method used for the carbon black determination (method A of ISO 1408:1995);
- f) the reference materials used to prepare the test mix;
- g) the ambient conditions in the laboratory during preparation of the test mix;
- h) the type of curemeter used, the defined time at which M_H was measured and the amplitude of oscillation used for the curemeter test, as defined in [Clause 7](#);