

AEROSPACE MATERIAL SPECIFICATION



AMS 2451/8

Issued

AUG 2000

Plating, Brush, Non-Cyanide Silver General Purpose

1. SCOPE:

1.1 Purpose:

This specification covers the engineering requirements and process for brush plating of non-cyanide silver by electrodeposition. It is used, in conjunction with AMS 2451, for silver deposits.

1.2 Application:

This process has been used typically to provide low electrical contact resistance, prevent galling or seizing of surfaces of parts, and corrosion protection, but usage is not limited to such applications.

1.3 Safety - Hazardous Materials:

See AMS 2451.

2. APPLICABLE DOCUMENTS:

See AMS 2451.

3. TECHNICAL REQUIREMENTS:

The requirements of AMS 2451 shall apply as herein amended.

3.1 Procedure:

3.1.1 Silver shall be electrodeposited from a non-cyanide silver brush plating solution in accordance with processing instructions from the solution manufacturer.

3.1.2 A preliminary strike or bonding layer of nickel and copper, palladium or gold may be used.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790