

**SAE** The Engineering Society  
For Advancing Mobility  
Land Sea Air and Space®  
**INTERNATIONAL**

400 Commonwealth Drive, Warrendale, PA 15096-0001

# AEROSPACE MATERIAL SPECIFICATION

**SAE** AMS-3200

REV  
G

Issued 1942-12-01

Revised 1990-04-01

Superseding AMS-3200F

Submitted for recognition as an American National Standard

## NITRILE (NBR) RUBBER Petroleum-Base Hydraulic Fluid Resistant 55 - 65

### 1. SCOPE:

- 1.1 Form: This specification covers a nitrile (NBR) rubber in the form of sheet, strip, tubing, extrusions, and molded shapes.
- 1.2 Application: Primarily for parts, such as seals and gaskets, requiring resistance to petroleum-base hydraulic fluids.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

### 2.1.1 Aerospace Material Specifications:

AMS-2279 - Tolerances, Rubber Products  
MAM-2279 - Tolerances, Metric, Rubber Products  
AMS-2810 - Identification and Packaging, Elastomeric Products

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

**SAE** AMS-3200 Revision G

2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

- ASTM D 297 - Rubber Products - Chemical Analysis
- ASTM D 395 - Rubber Property - Compression Set
- ASTM D 412 - Rubber Properties in Tension
- ASTM D 471 - Rubber Property - Effect of Liquids
- ASTM D 518 - Rubber Deterioration - Surface Cracking
- ASTM D 573 - Rubber - Deterioration in an Air Oven
- ASTM D 797 - Rubber Property - Young's Modulus at Normal and Subnormal Temperatures
- ASTM D 1149 - Rubber Deterioration - Surface Ozone Cracking in a Chamber (Flat Specimens)
- ASTM D 2137 - Rubber Property - Brittleness Point of Flexible Polymers and Coated Fabrics
- ASTM D 2240 - Rubber Property - Durometer Hardness

### 3. TECHNICAL REQUIREMENTS:

- 3.1 Material: Shall be a compound, based on an acrylonitrile-butadiene (NBR) elastomer, suitably cured to produce a product meeting the requirements of 3.2.
- 3.2 Properties: The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable:

#### 3.2.1 As Received:

- |           |  |                                |   |
|-----------|--|--------------------------------|---|
| 3.2.1.1   | Hardness, Durometer "A" or equivalent                          | 60 $\pm$ 5                     | ASTM D 2240   |
| 3.2.1.2   | Tensile Strength, minimum                                      | 1400 psi<br>(9.65 MPa)         | ASTM D 412, Die B or C  |
| 3.2.1.3   | Elongation, minimum  |                                | ASTM D 412, Die B or C  |
| 3.2.1.3.1 | For parts other than extrusions                                | 250%                           |   |
| 3.2.1.3.2 | For extruded parts   | 80% of Preproduction Value     |   |
| 3.2.1.4   | Specific Gravity   | Preproduction Value $\pm$ 0.02 | ASTM D 297  |
| 3.2.2     | <u>Oil Resistance</u> :<br>(Immediate Deteriorated Properties) |                                | ASTM D 471<br>Medium: ASTM Oil No. 3<br>Temperature: 100°C $\pm$ 1<br>(212°F $\pm$ 2) |
| 3.2.2.1   | Hardness Change, Durometer "A" or equivalent                   | -15 to +5                      | Time: 70 hours $\pm$ 0.5  |

**SAE** AMS-3200 Revision G

- 3.2.2.2 Tensile Strength Change, maximum -30%
- 3.2.2.3 Elongation Change, maximum -30%
- 3.2.2.4 Volume Change 0 to +25%
- 3.2.2.5 Decomposition None
- 3.2.2.6 Surface Tackiness None
- 3.2.3 Dry Heat Resistance: ASTM D 573  
 Temperature: 100°C ± 1 (212°F ± 2)  
 Time: 70 hours ± 0.5
- 3.2.3.1 Hardness Change, Durometer "A" or equivalent 0 to +15
- 3.2.3.2 Tensile Strength Change, maximum -10%
- 3.2.3.3 Elongation Change, maximum -45%
- 3.2.3.4 Bend (flat) No cracking or checking
- 3.2.4 Compression Set: ASTM D 395, Method B  
 Temperature: 100°C ± 1 (212°F ± 2)  
 Time: 70 hours ± 0.5
- Percent of Original Deflection, maximum 70
- 3.2.5 Low-Temperature Resistance:
- 3.2.5.1 Brittleness Pass ASTM D 2137, Method A  
 Temperature: -35°C ± 1 (-31°F ± 2)
- 3.2.5.2 Young's Modulus, maximum 30,000 psi (207 MPa) ASTM D 797  
 Temperature: -40°C ± 1 (-40°F ± 2)  
 (See 8.2)
- 3.2.6 Weathering: The product shall show no evidence of cracking when tested in accordance with ASTM D 1149 for 7 days at 40°C ± 1 (104°F ± 2). Test specimens shall be prepared and mounted in accordance with ASTM D 518, Method B.
- 3.2.7 Corrosion: The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service, determined by a procedure agreed upon by purchaser and vendor. Discoloration of metal shall not be considered objectionable.

**SAE** AMS-3200 Revision G

3.3 Quality: The product, as received by purchaser, shall be uniform in quality and condition, smooth, as free from foreign material as commercially practicable, and free from imperfections detrimental to usage of the product.

3.4 Tolerances: Shall conform to all applicable requirements of AMS-2279 or  
 0 MAM-2279.

#### 4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

#### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for the following requirements are acceptance tests and shall be performed on each lot:

Requirement	Paragraph
Hardness, as received	3.2.1.1
Tensile Strength, as received	3.2.1.2
Elongation, as received	3.2.1.3
Specific Gravity	3.2.1.4
Volume Change in oil	3.2.2.4
Compression Set	3.2.4

4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the first-article shipment of a product to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.