

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

SAE AMS 3357F

Issued 2-1-56
Revised 1-1-86

Superseding AMS 3357E

SILICONE (VMQ) RUBBER Lubricating Oil and Compression Set Resistant 65 - 75

1. SCOPE:

- 1.1 Form: This specification covers a silicone (VMQ) rubber in the form of sheet, strip, tubing, extrusions, and molded shapes.
- 1.2 Application: Primarily for rubber-like parts required to operate or seal from -55° to +230°C (-65° to +450°F), compounded especially for aircraft piston engine oil resistance and low compression set. Silicone elastomer is resistant to deterioration by weathering and by high-aniline-point petroleum-base oils and remains flexible over the temperature range noted. This material is not normally suitable for use in contact with gasoline or aromatic fuels and low-aniline-point petroleum-base fluids due to excessive swelling of the elastomer.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2279 - Tolerances, Rubber Products
MAM 2279 - Tolerances, Metric, Rubber Products
AMS 2350 - Standards and Test Methods
AMS 2810 - Identification and Packaging, Elastomeric Products

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM D297 - Rubber Products - Chemical Analysis
- ASTM D395 - Rubber Property - Compression Set
- ASTM D412 - Rubber Properties in Tension
- ASTM D471 - Rubber Property - Effect of Liquids
- ASTM D573 - Rubber - Deterioration in an Air Oven
- ASTM D624 - Rubber Property - Tear Resistance
- ASTM D797 - Rubber Property - Young's Modulus at Normal and Subnormal Temperatures
- ASTM D2137 - Rubber Property - Brittleness Point of Flexible Polymers and Coated Fabrics
- ASTM D2240 - Rubber Property - Durometer Hardness

3. TECHNICAL REQUIREMENTS:

- 3.1 Material: Shall be a compound based on a silicone (VMQ) rubber, suitably cured to produce a product meeting the requirements of 3.2.
- 3.2 Properties: The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable:

3.2.1 As Received:

- | | | | |
|---------|---|--------------------------------|----------------------------------|
| 3.2.1.1 | Hardness, Durometer "A" or equivalent | 70 \pm 5 | ASTM D2240 |
| 3.2.1.2 | Tensile Strength, min | 800 psi
(5.50 MPa) | ASTM D412, Die B or C |
| 3.2.1.3 | Elongation, min | 150% | ASTM D412, Die B or C |
| 3.2.1.4 | Tensile Stress at 50% Elongation, min | 200 psi
(1.40 MPa) | ASTM D412, Die B or C |
| 3.2.1.5 | Tear Strength, min | 60 lb per in.
(10.5 kN/m) | ASTM D624, Die B |
| 3.2.1.6 | Specific Gravity | Preproduction Value \pm 0.03 | ASTM D297 |
| 3.2.2 | <u>Petroleum Lubricating Oil Resistance:</u>
(Immediate Deteriorated Properties) | | ASTM D471 |
| | | Medium: | ASTM Oil No. 1 |
| | | Temperature: | 175°C \pm 3
(347°F \pm 5) |
| | | Time: | 70 hr \pm 0.5 |
| 3.2.2.1 | Hardness Change, Durometer "A" or equivalent | -10 to +5 | |
| 3.2.2.2 | Tensile Strength Change, max | -20% | |

- 3.2.2.3 Elongation Change, max -15%
- 3.2.2.4 Volume Change, max 0 to +15%
- 3.2.2.5 Decomposition None
- 3.2.2.6 Surface Tackiness None
- 3.2.3 Dry Heat Resistance:
 Ø ASTM D573
 Temperature: 225°C ± 3
 (437°F ± 5)
 Time: 22 hr ± 0.5
- 3.2.3.1 Hardness Change, Durometer "A" or equivalent -5 to +10
- 3.2.3.2 Tensile Strength Change, max -15%
- 3.2.3.3 Elongation Change, max -25%
- 3.2.3.4 Bend (flat) No cracking or checking
- 3.2.4 Compression Set:
 Ø ASTM D395, Method B
 Temperature: 175°C + 3
 (347°F + 5)
 Time: 22 hr ± 0.5
- 3.2.4.1 Percent of Original Deflection, max 35
- 3.2.5 Low-Temperature Resistance:
- 3.2.5.1 Brittleness Pass
 Ø ASTM D2137, Method A
 Temperature: -65°C + 3
 (-85°F + 5)
- 3.2.5.2 Young's Modulus, max 10,000 psi (69 MPa)
 Ø ASTM D797
 Temperature: -50°C + 3
 (-58°F + 5)
 Time: 5 hr ± 0.2
- 3.2.6 Weathering: The product shall have weather resistance acceptable to the purchaser, determined by a procedure agreed upon by purchaser and vendor.
 Ø
- 3.2.7 Corrosion: The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service, determined by a procedure agreed upon by purchaser and vendor. Discoloration of metal shall not be considered objectionable.
- 3.3 Quality: The product, as received by purchaser, shall be uniform in quality and condition, clean, smooth, as free from foreign materials as commercially practicable, and free from imperfections detrimental to usage of the product.
- 3.4 Tolerances: Shall conform to AMS 2279 or MAM 2279.
 Ø
4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each lot:

Requirement

Paragraph Reference

Hardness, as received	3.2.1.1
Tensile Strength, as received	3.2.1.2
Elongation, as received	3.2.1.3
Specific Gravity	3.2.1.6
Petroleum Lubricating Oil Resistance	3.2.2
Compression Set	3.2.4

- 4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the initial shipment of the product to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

- 4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be as follows:

- 4.3.1 For Acceptance Tests: Sufficient product shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three. If specimens cannot be prepared from the product, ASTM test specimens prepared from the same batch and state of cure shall be used. When the product supplied is an extrusion of such shape that suitable test specimens cannot be cut from the product, a separate flat strip test sample shall be supplied on request. This strip shall be prepared from tubing 1 in. + 0.063 (25 mm + 1.60) in OD by 0.075 in. + 0.008 (1.90 mm + 0.20) in wall thickness, mechanically split and flattened into a strip while being extruded, and cured in the same manner as production material. When the product is a molded shape from which test specimens cannot be cut, a slab 6 x 6 in. (150 x 150 mm) by 0.080 in. + 0.008 (2.00 mm + 0.020) molded from the same batch of compound shall be supplied upon request.