



400 Commonwealth Dr., Warrendale, PA 15096

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

AMS 3839C
Superseding AMS 3839B

Issued 9-1-65
Revised 10-1-85

FABRIC, WIRE-REINFORCED ASBESTOS Polytetrafluoroethylene Impregnated, Sintered

1. SCOPE:

- 1.1 Form: This specification covers one type of wire-reinforced asbestos fabric impregnated with polytetrafluoroethylene resin in the form of woven sheet or strip and braided tubing or strip.
- 1.2 Application: Primarily as an anti-chafing cushion between metal tubes and tube clips operating in service up to 260°C (500°F).
- 1.3 WARNING: Numerous scientific studies have determined that asbestos presents a health hazard to those who are exposed to asbestos-containing products.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D299 - Asbestos Yarns

ASTM D792 - Specific Gravity and Density of Plastics by Displacement

ASTM F36 - Compressibility and Recovery of Gasket Materials

- 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Material and Fabrication: The fabric shall be made from selected long-fiber, Grade A or better (Ref. ASTM D299) chrysotile asbestos yarn woven or braided into the desired form, with each yarn in the fabric being reinforced with brass, copper, or corrosion-resistant steel wire and the fabric being impregnated with polytetrafluoroethylene resin and sintered.

3.2 Color: Shall be white to dark brown.

3.3 Properties: The fabric shall conform to the following requirements; tests shall be performed on the fabric supplied and in accordance with specified methods:

3.3.1 Specific Gravity, 23°/23°C (73°/73°F)	1.80 - 2.25	ASTM D792, Method A
---	-------------	------------------------

3.3.2 Compressibility	12 - 25%	ASTM F36, Procedure A
-----------------------	----------	--------------------------

3.3.2.1 Recovery, min	15%	
-----------------------	-----	--

3.3.3 Weight Loss at 315°C (600°F), based on original dry weight, max	5%	4.5.1
--	----	-------

3.3.4 Weight Loss at 480°C (900°F), based on original dry weight	45 - 55%	4.5.1
---	----------	-------

3.3.5 Brittleness After Sintering	Bend flat with no breaks in fabric	4.5.2
-----------------------------------	--	-------

3.3.6 Corrosion: The fabric shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable. Method of test and acceptance standards shall be as agreed upon by purchaser and vendor.

3.4 Quality: Fabric, as received by purchaser, shall be uniform in quality and condition, clean, sound, and free from foreign materials and from imperfections detrimental to usage of the fabric.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the fabric shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the fabric conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for specific gravity (3.3.1), compressibility and recovery (3.3.2), and weight loss on heating (3.3.3 and 3.3.4) are classified as acceptance tests and shall be performed on each lot.

4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the initial shipment of fabric to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be as follows; a lot shall be all fabric of the same size and form produced in a continuous run and presented for vendor's inspection at one time:

Requirement	Paragraph Reference	Number of Determinations	
		Acceptance Tests	Preproduction Tests
Specific Gravity	3.3.1	1	3
Compressibility and Recovery	3.3.2	2	3
Weight Loss	3.3.3, 3.3.4	1	3
Brittleness	3.3.5	--	3

4.4 Approval:

4.4.1 Sample fabric shall be approved by purchaser before fabric for production use is supplied, unless such approval be waived by purchaser. Results of tests on production fabric shall be essentially equivalent to those on the approved sample.

4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production fabric which are essentially the same as those used on the approved sample fabric. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material, processing, or both and, when requested, sample fabric. Production fabric made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Test Methods:

- 4.5.1 Weight Loss: Place a 2-g \pm 0.1 sample in a tared crucible and heat at $105^{\circ}\text{C} \pm 1$ ($220^{\circ}\text{F} \pm 2$) to constant weight (original dry weight) at room temperature. Heat the crucible and contents to $315^{\circ}\text{C} \pm 5$ ($600^{\circ}\text{F} \pm 10$), hold at heat for 24 hr \pm 0.3, cool in a desiccator, and reweigh. Reheat the crucible and contents to $480^{\circ}\text{C} \pm 15$ ($900^{\circ}\text{F} \pm 25$), hold at heat for 3 hr \pm 0.3, cool, weigh, and calculate the weight losses occurring during the 315°C (600°F) and the 480°C (900°F) heatings.
- 4.5.2 Brittleness After Sintering: Heat a specimen to $315^{\circ}\text{C} \pm 5$ ($600^{\circ}\text{F} \pm 10$) and hold at heat for 24 hr \pm 0.3. Transfer the specimen to an oven which is at $385^{\circ}\text{C} \pm 15$ ($725^{\circ}\text{F} \pm 25$), heat to $385^{\circ}\text{C} \pm 15$ ($725^{\circ}\text{F} \pm 25$), hold at heat for 1 hr \pm 0.1, and quench in water. Bend the specimen flat on itself. Specimens of tubing shall be split open and bent with the outside surface of the tube wall on the inside of the bend. Formed, raised edges may be removed from strip to facilitate bending.

4.6 Reports:

- 4.6.1 The vendor of fabric shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance test requirements and stating that the fabric conforms to the other technical requirements of this specification. This report shall include the purchase order number, AMS 3839C, lot number, vendor's material designation, form, size, and quantity.
- 4.6.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 3839C, contractor or other direct supplier of fabric, supplier's material designation, part number, and quantity. When fabric for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of fabric to determine conformance to the requirements of this specification and shall include in the report either a statement that the fabric conforms or copies of laboratory reports showing the results of tests to determine conformance.
- 4.7 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the fabric may be based on the results of testing three additional specimens for each original non-conforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the fabric represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Packaging and Identification:

- 5.1.1 Packaging shall be accomplished in such a manner as to ensure that the fabric, during shipment and storage, will be protected from exposure to weather or any other normal hazard.