

# AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard



AMS 4007D

Issued	MAR 1974
Revised	APR 1987
Noncurrent	SEP 1991
Cancelled	AUG 1999

Superseding AMS 4007C

Aluminum Alloy Foil  
4.4Cu - 1.5Mg - 0.6Mn (2024-0)

## CANCELLATION NOTICE

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of August 1999. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications.

SAENORM.COM : Click to view the full PDF of AMS4007d

SAE Technical Standards Board Rules provide that "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1999 Society of Automotive Engineers, Inc.  
All rights reserved.

QUESTIONS REGARDING THIS DOCUMENT:  
TO PLACE A DOCUMENT ORDER:  
SAE WEB ADDRESS:

(724) 772-7161  
(724) 776-4970  
<http://www.sae.org>

FAX: (724) 776-0243  
FAX: (724) 776-0790



Reproduced By GLOBAL  
ENGINEERING DOCUMENTS  
With The Permission Of SAE  
Under Royalty Agreement

Printed in U S A

**1. SCOPE:****1.1 Form:**

This specification covers an aluminum alloy in the form of foil.

**1.2 Application:**

Primarily for fabrication of diffusion-bonded, fiber-reinforced-composite tape, sheet, plate, and other structural forms.

**2. APPLICABLE DOCUMENTS:**

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

**2.1 SAE Publications:**

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

**2.1.1 Aerospace Material Specifications:**

- AMS 2350 Standards and Test Methods
- AMS 2355 Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings
- MAM 2355 Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings, Metric (SI) Units
- AMS 2770 Heat Treatment of Aluminum and Aluminum Alloys

**2.2 ASTM Publications:**

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103.

- ASTM E252 Thickness of Thin Foil and Film by Weighing
- ASTM E345 Tension Testing of Metallic Foil

**2.3 U.S. Government Publications:**

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

**2.3.1 Military Standards:**

- MIL-STD-649 Aluminum and Magnesium Products, Preparation for Shipment and Storage

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Composition:

Shall conform to the following percentages by weight, determined in accordance with AMS 2355 or MAM 2355:

	min	max
Copper	3.8	4.9
Magnesium	1.2	1.8
Manganese	0.30	0.9
Iron	--	0.50
Silicon	--	0.50
Zinc	--	0.25
Titanium	--	0.15
Chromium	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

## 3.2 Condition:

Annealed.

## 3.3 Properties:

Foil shall conform to the following requirements; tensile strength shall be determined in accordance with ASTM E345 and bending shall be performed in accordance with AMS 2355 or MAM 2355.

## 3.3.1 Tensile Properties As Annealed:

Tensile Strength, max                      32,000 psi (220 MPa)

## 3.3.2 Properties After Solution Heat Treatment: Foil after solution heat treatment in accordance with AMS 2770 and aging for not less than 4 days at room temperature shall have the following properties:

## 3.3.2.1 Tensile Properties:

Tensile Strength, min                      62,000 psi (425 MPa)

3.3.2.2 Bending: Foil shall withstand, without cracking, bending through an angle of 180 deg around a diameter equal to four times the nominal thickness of the foil with axis of bend parallel to the direction of rolling.

#### 3.4 Quality:

Foil, as received by purchaser, shall be uniform in quality and condition, sound, and free from holes, tears, and other discontinuities and from internal imperfections detrimental to usage of the foil. Dents, ripples, kinks, and sharp bends in the foil are acceptable provided they are located within 0.050 in. (1.25 mm) of an edge or are less than 0.30 in. (0.75 mm) deep.

3.4.1 Foil shall be free from oil, grease, and dirt to the extent that a clean, white rag wiped on the foil for several passes shall pick up no perceptible liquid or solid contaminants.

#### 3.5 Tolerances:

Shall be as follows:

3.5.1 Thickness: Shall not deviate from the specified thickness by more than  $\pm 10\%$ , determined on two specimens for each nominal thickness by instrument measurement or by the weighing method specified for thin foil in ASTM E252.

3.5.1.1 When a dispute occurs between purchaser and vendor over thickness values, thickness determined by the weighing method of ASTM E252 shall apply. For such calculations, density shall be taken as 0.101 lb per cu in. (2.78 Mg/m<sup>3</sup>).

3.5.2 Width: Shall be within  $\pm 0.032$  in. (0.80 mm) of that specified.

#### 4. QUALITY ASSURANCE PROVISIONS:

##### 4.1 Responsibility for Inspection:

The vendor of foil shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the foil conforms to the requirements of this specification.

##### 4.2 Classification of Tests:

Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each lot.

##### 4.3 Sampling:

One sample shall be selected for each 2000 lb (900 kg) or fraction thereof from each lot; however, not more than one sample is required from a coil.

4.3.1 An inspection lot shall consist of an identifiable quantity of foil of the same alloy, temper, finish, and nominal dimensions presented for vendor's inspection at one time.

#### 4.4 Reports:

4.4.1 The vendor of foil shall furnish with each shipment a report showing the results of tests to determine conformance to the technical requirements of this specification. This report shall include the purchase order number, AMS 4007B, lot number, size, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 4007B, contractor or other direct supplier of foil, part number, and quantity. When foil for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of foil to determine conformance to the requirements of this specification and shall include in the report either a statement that the foil conforms or copies of laboratory reports showing the results of tests to determine conformance.

#### 4.5 Resampling and Retesting:

If any specimen used in the above tests fails to meet the specified requirements, disposition of the foil may be based on the results of testing two additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the foil represented and no additional testing shall be permitted. Results of all tests shall be reported.

### 5. PREPARATION FOR DELIVERY:

#### 5.1 Packaging and Identification:

5.1.1 Foil shall be furnished in rolls, wound on 3 in. (75 mm) diameter cores; the diameter of the rolls shall be not less than 6 in. (150 mm) nor more than 34 in. (850 mm). The foil in each roll, when possible, shall be in one continuous length but may contain a maximum of one splice for every 3000 lineal feet (915 mm) or fraction thereof per roll. Splices shall be made with pressure-sensitive tape or by electric or ultrasonic welding. Splices shall be marked with a colored tape or equivalent that shall extend over the edge of the roll so as to be easily seen at the edges of the roll. Foil condition and coiling shall be such that complete uncoiling may be accomplished with no resulting tearing or other damage to the foil. Each roll shall be closely wrapped in waterproof paper.