

AERONAUTICAL MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

AMS 4146

Issued 6-30-60
Revised

ALUMINUM ALLOY FORGINGS 11Mg - 0.6Si - 0.3Cu - 0.25Cr (6061-T4)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. FORM: Forgings and forging stock.
3. APPLICATION: Primarily for forged parts which will be welded or brazed to form assemblies and then given further heat treatment to develop full strength of which the alloy is capable.
4. COMPOSITION:

Magnesium	0.8 - 1.2
Silicon	0.40 - 0.8
Copper	0.15 - 0.40
Chromium	0.15 - 0.35
Iron	0.7 max
Zinc	0.25 max
Manganese	0.15 max
Titanium	0.15 max
Other Impurities, each	0.05 max
Other Impurities, total	0.15 max
Aluminum	remainder

5. CONDITION:
 - 5.1 Die Forgings and Rolled Rings: Solution heat treated. Quenching from the solution temperature shall be at a rate fast enough for the material to meet the following requirements, but shall be as slow as practicable in order to keep internal stresses at a minimum.
 - 5.2 Forging Stock: As fabricated.
6. TECHNICAL REQUIREMENTS:
 - 6.1 Die Forgings and Rolled Rings:
 - 6.1.1 Hardness: Forgings shall have hardness of Brinell 50 - 60, using 500 kg load and 10 mm ball or 1000 kg load and 9/16 in. ball, or Brinell 55 - 85 using 1000 kg load and 10 mm ball.
 - 6.1.2 Properties After Heat Treatment: Forgings after proper precipitation heat treatment shall conform to the following requirements:
 - 6.1.2.1 Tensile Properties:

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no attempt to adhere to any SAE standard or recommended practice, and no commitment is made by the Society or the Board that any report will be adopted by any technical committee. The Board and its Committees will not investigate or consider to conform to or be guided by any technical report. In formulating and approving any technical report, the Board and its Committees will not consider liability for infringement of patents." Prospective users of the report are responsible for protecting themselves against liability for infringement of patents.

6.1.2.1.1 Test Specimens: Test specimens, machined from separately forged coupons or from forging stock representing the forgings and in either case heat treated with the forgings, or machined from prolongations on heat treated forgings, shall conform to the following requirements:

Tensile Strength, psi	38,000 min
Yield Strength at 0.2% Offset or at 0.0111 in.	
in 2 in. Extension Under Load ($E = 9,900,000$), psi	35,000 min
Elongation, % in 4D	10 min

6.1.2.1.2 Die forgings, With Grain Flow: When test specimens are machined from forgings not over 4 in. in thickness with the axis approximately parallel to the forging flow lines, the tensile properties shall conform to those specified in 6.1.2.1.1, except that elongation may be as low as 7%, unless otherwise agreed upon by purchaser and vendor.

6.1.2.1.3 Die forgings, Across Grain Flow: When test specimens are machined from die forgings not over 4 in. in thickness so that the axis is other than approximately parallel to the forging flow lines, the tensile properties shall conform to the following requirements:

Tensile Strength, psi	38,000 min
Yield Strength at 0.2% Offset or at 0.0111 in.	
in 2 in. Extension Under Load ($E = 9,900,000$), psi	35,000 min
Elongation, % in 4D	5 min

6.1.2.1.4 Rolled Rings, Tangential: When test specimens are machined from rolled rings not over 2-1/2 in. in thickness with axis tangential to the ring OD (axis parallel to direction of rolling), the tensile properties shall conform to those specified in 6.1.2.1.1, unless otherwise agreed upon by purchaser and vendor.

6.1.2.1.5 Rolled Rings, Axial: When test specimens are machined from rolled rings not over 2-1/2 in. in thickness with axis parallel to axis of ring (axis transverse to direction of rolling), the tensile properties shall conform to those specified in 6.1.2.1.1, except that elongation may be as low as 8%, unless otherwise agreed upon by purchaser and vendor.

6.1.2.2 Hardness: forgings shall have hardness not lower than Brinell 80 using 500 kg load and 10 mm ball or 1000 kg load and 9/16 in. ball, or not lower than Brinell 85 using 1000 kg load and 10 mm ball.

6.2 Forging Stock:

6.2.1 When a sample of stock is forged to a test coupon and heat treated in the same manner as forgings, including proper precipitation heat treatment, a tensile test specimen taken from the heat treated coupon shall have properties not lower than those specified in 6.1.2.1.1 and 6.1.2.2. If a test specimen taken from the stock after heat treatment in the same manner as forgings, including proper precipitation heat treatment, has properties not lower than those specified in 6.1.2.1.1 and 6.1.2.2, the test shall be accepted as equivalent to the test of a forged coupon. Neither of these tests is required in routine inspection.