

AEROSPACE MATERIAL SPECIFICATION

SAE AMS4244B

Issued 1987-01
Revised 2008-07

Superseding AMS4244A

Aluminum Alloy, Welding Wire
4.6Cu - 0.35Mn - 0.25Mg - 0.22Ti
For Welding A206.0 Type Alloys

RATIONALE

AMS4244B results from a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of two types of welding wire.

1.2 Application

This wire has been used typically as filler metal for gas-metal-arc and gas-tungsten-arc welding of aluminum alloy castings having similar composition (206.0 and A206.0) and requiring response to heat treatment, properties, and corrosion resistance in the weld zone comparable to those of the castings, but usage is not limited to such applications.

1.3 Classification

Wire supplied to this specification is classified as follows:

Type 1 - As Extruded and Sized

Type 2 - As Drawn

1.3.1 Unless a specific type is ordered, either type may be supplied.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2008 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)

Tel: 724-776-4970 (outside USA)

Fax: 724-776-0790

Email: CustomerService@sae.org

<http://www.sae.org>

SAE WEB ADDRESS:

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2355	Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings
AMS2813	Packaging and Marking of Packages of Welding Wire, Standard Method
AMS2814	Packaging and Marking of Packages of Welding Wire, Premium Quality
AMS2816	Identification, Welding Wire, Tab Marking Method
AMS2819	Identification, Welding Wire, Direct Color Code System
ARP1876	Weldability Test for Weld Filler Metal Wire
ARP4926	Alloy Verification and Chemical Composition Inspection of Welding Wire

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2355.

TABLE 1 - COMPOSITION

Element	min	max
Silicon	--	0.05
Iron	--	0.10
Copper	4.2	5.0
Manganese	0.20	0.50
Magnesium	0.15	0.35
Nickel	--	0.05
Zinc	--	0.10
Titanium	0.15	0.30
Tin	--	0.05
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.1.1 Chemical analysis of initial ingot, bar, or rod stock before drawing is acceptable provided the processes used for drawing or rolling, annealing, and cleaning are controlled to ensure continued conformance to composition requirements, and the facility employs procedures to ensure traceability of wire to the originally analyzed source.

3.2 Condition

Wire may be made by any method unless a specific method is specified. Wire shall be in a temper and with a surface finish which will provide proper feeding of the wire in machine welding equipment.

3.3 Fabrication

3.3.1 Butt welding is permissible provided both ends to be joined are identified by chemical analysis or the repair is made at the wire processing station. The butt weld shall not interfere with uniform, uninterrupted feeding of the wire in machine welding equipment.

3.3.2 Drawing compounds, oxides, dirt, oil, and other foreign material shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.4 Weldability

Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.

3.5 Quality

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.6 Sizes and Tolerances

Wire shall be supplied in the sizes and to the tolerances shown in 3.6.1 and 3.6.2.

3.6.1 Diameter

3.6.1.1 Extruded Wire

Shall be as shown in Table 2:

TABLE 2A - SIZES AND DIAMETER TOLERANCES, INCH/POUND UNITS

Form	Nominal Diameter Inch	Tolerance Inch plus	Tolerance Inch minus
Cut Lengths	0.047, 0.062, 0.094, 0.125	0.007	0.007
Spools	0.030, 0.035, 0.047, 0.062, 0.094	0.002	0.002

TABLE 2B - SIZES AND DIAMETER TOLERANCES, SI UNITS

Form	Nominal Diameter Millimeters	Tolerance Millimeters plus	Tolerance Millimeters minus
Cut Lengths	1.19, 1.57, 2.39, 3.18	0.18	0.18
Spools	0.76, 0.89, 1.19, 1.57, 2.39	0.05	0.05

3.6.1.2 Drawn Wire

Shall be as shown in Table 3:

TABLE 3A - SIZES AND DIAMETER TOLERANCES, INCH/POUND UNITS

Form	Nominal Diameter Inch	Tolerance Inch plus	Tolerance Inch minus
Cut Lengths	0.047, 0.062, 0.094, 0.125	0.003	0.003
Spools	0.030, 0.035, 0.047	0.001	0.002
Spools	0.062, 0.094	0.002	0.002

TABLE 3B - SIZES AND DIAMETER TOLERANCES, SI UNITS

Form	Nominal Diameter Millimeters	Tolerance Millimeters	Tolerance Millimeters
		plus	minus
Cut Lengths	1.19, 1.57, 2.39, 3.18	0.08	0.08
Spools	0.76, 0.89, 1.19	0.02	0.05
Spools	1.57, 2.39	0.05	0.05

3.6.2 Length

Cut lengths shall be furnished in 36-inch (914-mm) lengths and shall not vary more than +0, -1 inch (+0, -25 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1) and sizes and tolerances (3.6) are acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests

Weldability (3.4) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

Shall be in accordance with AMS2355.

4.4 Reports

The vendor of wire shall furnish with each shipment a report stating that the wire conforms to the chemical composition and other technical requirements. This report shall include the purchase order number, AMS4244B, lot number, nominal size, and quantity from each lot.

4.5 Resampling and Retesting

Shall be in accordance with AMS2355.

5. PREPARATION FOR DELIVERY

5.1 Wire

Wire shall be supplied either on spools in one continuous length for machine welding, or in cut lengths for manual welding as ordered. Wire on each spool or in each package of cut lengths shall be from the same heat of alloy.