

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 4575A

Issued 11-1-49

Revised 6-15-50

NICKEL-COPPER ALLOY TUBING, BRAZED, CORROSION RESISTANT
67Ni - 30Cu
Annealed

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. FORM: Copper furnace brazed.

3. APPLICATION: Primarily for fluid lines, such as primer and fuel lines, requiring corrosion resistance with strength relatively high for non-ferrous alloys.

4. COMPOSITION:

Nickel + Cobalt	63.00 - 70.00
Iron	2.50 max
Manganese	2.00 max
Cobalt, if determined	1.00 max
Silicon	0.50 max
Aluminum	0.50 max
Carbon	0.30 max
Sulfur	0.02 max
Copper	remainder

5. CONDITION: Cold drawn after brazing, and annealed.

6. TECHNICAL REQUIREMENTS:

6.1 Physical Properties:

Tensile Strength, psi	85,000 max
Elongation, % in 2 in.	32 min

6.2 Flarability: Tubing shall be capable of being flared without formation of cracks or other visible defects. Specimens for flaring may be cut from any portion of the tube, or an entire tube may be used as a specimen. The end of the specimen to be flared shall be cut square, with the cut end smooth and free from burrs, but not rounded. The specimen shall, at room temperature, be forced axially with steady pressure over a hardened and polished tapered steel pin having a 74 degree included angle, to produce a flare having the permanent expanded OD specified in the following table:

Nominal OD Inch	Expanded OD Inch, min
0.125	0.224
0.188	0.290
0.250	0.359
0.312	0.421
0.375	0.484
0.500	0.656
0.625	0.781