



# AEROSPACE MATERIAL

Society of Automotive Engineers, Inc.

400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

# SPECIFICATION

## AMS 5565F

Superseding AMS 5565E

Issued 11-1-44

Revised 1-15-76

UNS S30400

STEEL TUBING, WELDED, CORROSION RESISTANT  
19Cr - 9.5Ni (SAE 30304)

### 1. SCOPE:

1.1 Form: This specification covers a corrosion-resistant steel in the form of welded tubing.

1.2 Application: Primarily for parts and assemblies such as fluid-conducting lines not subjected to high pressure, requiring good corrosion resistance. Welding, brazing, or other exposure to temperatures over 800° F (427° C) during fabrication may impair corrosion resistance.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

#### 2.1.1 Aerospace Material Specifications:

AMS 2243 - Tolerances, Corrosion and Heat Resistant Steel Tubing

AMS 2248 - Chemical Check Analysis Limits, Wrought Heat and Corrosion Resistant Steels and Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Alloys, Wrought Products Except Forgings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A262 - Detecting Susceptibility to Intergranular Attack in Stainless Steels

ASTM A370 - Mechanical Testing of Steel Products

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

#### 2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

#### 2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

### 3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

SAE Technical Board rules provide that: "All technical reports, including standards, approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report, in formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

	min	max
Carbon	--	0.08
Manganese	--	2.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	18.00 -	20.00
Nickel	8.00 -	11.00
Molybdenum	--	0.75
Copper	--	0.75

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Condition: Solution heat treated free from continuous carbide network and descaled.

3.3 Fabrication: Tubing 2.00 in. (50.8 mm) and under in nominal OD shall be cold worked after welding. Any surface finishing operation applied to remove objectionable pits and surface blemishes shall be performed prior to final solution heat treatment. A light polish to improve surface appearance may be employed after solution heat treatment. Passivation shall follow any polishing treatment.

3.4 Properties: Tubing shall conform to the following requirements; tensile and bend testing shall be performed in accordance with ASTM A370:

3.4.1 Tensile Properties: Shall be as specified in Table I:

TABLE I

Nominal OD Inches	Nominal Wall Thickness Inches	Tensile Strength psi, max	Elongation in 2 in., %, min	
			Strip	Full Tube
Up to 0.188, incl	Up to 0.016, incl	115,000	--	35
	Over 0.016	100,000	--	40
Over 0.188 to 0.500, incl	Up to 0.010, incl	110,000	32	37
	Over 0.010	100,000	35	40
Over 0.500	Up to 0.010, incl	100,000	27	32
	Over 0.010	100,000	30	35

TABLE I (SI)

Nominal OD Millimetres	Nominal Wall Thickness Millimetres	Tensile Strength MPA, max	Elongation in 50.8 mm, %, min	
			Strip	Full Tube
Up to 4.78, incl	Up to 0.41, incl	793	--	35
	Over 0.41	690	--	40
Over 4.78 to 12.70, incl	Up to 0.25, incl	758	32	37
	Over 0.25	690	35	40
Over 12.70	Up to 0.25, incl	690	27	32
	Over 0.25	690	30	35

3.4.2 **Flarability:** Tubing shall withstand flaring at room temperature, without formation of cracks or other visible defects, by being forced axially with steady pressure over a hardened and polished tapered steel pin having a 74 deg (1.29 rad) included angle to produce a flare having a permanent expanded OD not less than that specified in Table II.

TABLE II

Nominal OD Inches	Expanded OD Inches	Nominal OD Inches	Expanded OD Inches
0.125	0.200	0.750	0.937
0.188	0.290	1.000	1.187
0.250	0.359	1.250	1.500
0.312	0.421	1.500	1.721
0.375	0.484	1.750	2.106
0.500	0.656	2.000	2.356
0.625	0.781		

TABLE II (SI)

Nominal OD Millimetres	Expanded OD Millimetres	Nominal OD Millimetres	Expanded OD Millimetres
3.18	5.08	19.05	23.80
4.78	7.37	25.40	30.15
6.35	9.12	31.75	38.10
7.92	10.69	38.10	43.71
9.52	12.29	44.45	53.49
12.70	16.66	50.80	59.84
15.88	19.84		

3.4.2.1 Tubing with nominal OD between any two standard sizes given in 3.4.2 shall take the same percentage flare as shown for the larger of the two sizes.

3.4.2.2 Tubing with nominal OD greater than 2.000 in. (50.80 mm) or less than 0.125 in. (3.18 mm) shall have flarability as agreed upon by purchaser and vendor.

3.4.3 **Embrittlement:** Tubing, as received, shall pass the copper/copper sulfate/sulfuric acid test performed in accordance with ASTM A262, Practice E, without evidence of intercrystalline surface attack. After exposure, full cross-sectional specimens of tubing 0.625 in. (15.88 mm) or less in nominal OD shall be flattened to a total thickness under load of three times the wall thickness of the tubing and 1 in. (25 mm) long specimens of tubing over 0.625 in. (15.88 mm) in nominal OD shall be split and bent 180 deg (3.14 rad), with outside surface of tube on inside of bend, around a diameter equal to the nominal wall thickness without showing cracks or other defects. In either flattening or bending, the fold shall be made parallel to the axis of the tube, and shall coincide with the weld.

3.4.4 **Pressure Test:** Tubing shall show no bulges, leaks, or other defects when subjected to an internal hydrostatic pressure, based on nominal dimensions, sufficient to cause a tensile stress of 20,000 psi (138 MPa) in the tubing wall.

3.5 **Quality:** Tubing shall be uniform in quality and condition and shall have a finish conforming to the best practice for high quality tubing. It shall be smooth, clean, and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other injurious conditions. Surface imperfections such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified for wall thickness but removal of such surface imperfections is not required.

- 3.6 If beads are present at the welds on the inner surfaces of tubing over 2.00 in. (50.8 mm) in nominal OD, such beads shall be not thicker than 0.010 in. (0.25 mm), unless otherwise specified. The outer surfaces of all tubing and the inner surfaces of tubing 2.00 in. (50.8 mm) and under in nominal OD shall be free from beads.
- 3.7 Sizes: Except when exact lengths or multiples of exact lengths are ordered, tubing will be acceptable in mill lengths of 6 - 20 ft (1.8 - 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).
- 3.8 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2243.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection: The vendor of tubing shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the tubing conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests to determine conformance to composition (3.1), tensile property (3.4.1), and tolerance (3.8) requirements are classified as acceptance or routine control tests.
- 4.2.2 Qualification Tests: Tests to determine conformance to flarability (3.4.2), embrittlement (3.4.3), and pressure test (3.4.4) requirements are classified as qualification or periodic control tests.
- 4.2.2.1 For direct U.S. Military procurement, qualification test material and supporting test data shall be submitted to the cognizant qualification agency as directed by the request for procurement, the procuring activity, or the contracting officer.
- 4.3 Sampling: Shall be in accordance with AMS 2371 and the following:
- 4.3.1 Specimens for flarability test may be cut from any portion of a tube or an entire tube may be used as a specimen. The end of the specimen to be flared shall be cut square, with the cut end smooth and free from burrs, and not rounded.
- 4.4 Reports:
- 4.4.1 The vendor of tubing shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat in the shipment, and for tensile properties of each size from each heat, and stating that the tubing conforms to the other technical requirements of this specification. This report shall include the purchase order number, heat number, material specification number and its revision letter, size, and quantity from each heat.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of tubing, part number, and quantity. When tubing for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of tubing to determine conformance to the requirements of this specification, and shall include in the report a statement that the tubing conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.