



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.

TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 10001

AMS 5600A

Superseding AMS 5600

Issued 11-1-68

Revised 5-1-70

STEEL SHEET, CORROSION RESISTANT, LAMINATED, EDGE BONDED

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for shims of special shapes in which the thickness is to be adjusted by removal of laminations as required.
3. **COMPOSITION:**

	min	max
Carbon	--	0.15
Manganese	--	2.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	17.00 - 19.00	
Nickel	8.00 - 10.00	
Molybdenum	--	0.50
Copper	--	0.50

- 3.1.1 **Check Analysis:** Composition variations shall meet the requirements of the latest issue of AMS 2248.
- 3.2 **Adhesive:** Shall be of a composition which will meet the fabrication and quality requirements of this specification.
4. **FABRICATION:** Laminated shim stock shall be fabricated from corrosion resistant steel laminations in the annealed or 1/4 hard temper. Stock shall consist completely of laminations 0.002 in. $\pm$ 0.0002 thick or 0.003 in. $\pm$ 0.0003 thick, or partly of such laminations in combination with a single thicker lamination, as ordered, precut to the desired shape, stacked to the desired thickness, and then bonded on the outside edge with adhesive.
5. **QUALITY:**
 - 5.1 The product shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.
 - 5.2 Laminations shall be bonded together in such a manner that normal handling shall not cause separation of laminations. The layers shall be capable of being readily peeled.

SAE Technical Board rules provide that: "All technical reports, including standards, approved practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."