

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard



AMS 5848B

Issued JAN 1987
Revised APR 1997

Superseding AMS 5848A

Steel, Corrosion Resistant, Bars, Wire, Forgings, Extrusions, Tubing, and Rings
Wear and Galling Resistant
8.0Mn - 4.0Si - 17Cr - 8.5Ni - 0.13N
Solution Heat Treated

UNS S21800

1. SCOPE:

1.1 Form:

This specification covers a corrosion-resistant steel in the form of bars, wire, forgings, extrusions, mechanical tubing, flash welded rings, and stock for forging, extruding, or flash welded rings.

1.2 Application:

These products have been used typically for parts requiring wear, galling, and corrosion resistance up to 950 °F (510 °C), but usage is not limited to such applications. Welding, brazing, or other exposure to temperatures over 950 °F (510 °C) during fabrication may impair corrosion resistance.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2241	Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
MAM 2241	Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
AMS 2243	Tolerances, Corrosion and Heat Resistant Steel Tubing
MAM 2243	Tolerances, Metric, Corrosion and Heat Resistant Steel Tubing
AMS 2248	Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1998 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7154
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.1 (Continued):

AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2374	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steel and Alloy Forgings
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
AMS 2808	Identification, Forgings
AMS 7490	Rings, Flash Welded, Corrosion and Heat Resistant Austenitic Steels, Austenitic-Type Iron, Nickel, or Cobalt Alloys, or Precipitation-Hardenable Alloys

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM A 262	Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels
ASTM A 370	Mechanical Testing of Steel Products
ASTM E 353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.10
Manganese	7.00	9.00
Silicon	3.50	4.50
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	16.00	18.00
Nickel	8.00	9.00
Nitrogen	0.08	0.18
Molybdenum	--	0.75
Copper	--	0.75

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Bars, Wire, Forgings, Extrusions, Mechanical Tubing, and Flash Welded Rings: Solution heat treated free from continuous carbide network.

3.2.1.1 Bars and Wire:

3.2.1.1.1 All hexagons, other bars 2.75 inches (69.8 mm) and under in nominal diameter or distance between parallel sides, and wire shall be cold finished.

3.2.1.1.2 Bars, other than hexagons, over 2.75 inches (69.8 mm) in nominal diameter or distance between parallel sides shall be hot finished.

3.2.1.2 Mechanical Tubing: Shall be cold finished.

3.2.1.3 Flash Welded Rings: Shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS 7490.

3.2.2 Stock for Forging, Extruding, or Flash Welded Rings: As ordered by the forging, extrusion, or flash welded ring manufacturer.

3.3 Heat Treatment:

Bars, wire, forgings, extrusions, mechanical tubing, and flash welded rings shall be solution heat treated by heating within the range 1925 to 1975 °F (1052 to 1079 °C), holding at heat for a time commensurate with section thickness, and cooling at a rate equivalent to an air cool or faster.

3.4 Properties:

The product shall conform to the following requirements; tensile and hardness testing shall be performed in accordance with ASTM A 370.

3.4.1 Bars, Wire, Forgings, Extrusions, Mechanical Tubing, and Flash Welded Rings:

3.4.1.1 Tensile Properties: Shall be as shown in Table 2 and Table 3.

3.4.1.1.1 Product 0.50 Inch (12.7 mm) and Under in Nominal Section Thickness: Shall be as shown in Table 2.

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	105 ksi (724 MPa)
Yield Strength at 0.2% Offset	55.0 ksi (379 MPa)
Elongation in 4D	35%
Reduction of Area	55%

- 3.4.1.1.2 Product Over 0.50 Inch (12.7 mm) in Nominal Section Thickness: Shall be as shown in Table 3.

TABLE 3 - Minimum Tensile Properties

Property	Value
Tensile Strength	95.0 ksi (655 MPa)
Yield Strength at 0.2% Offset	50.0 ksi (345 MPa)
Elongation in 4D	35%
Reduction of Area	55%

- 3.4.1.2 Hardness: Shall be as follows, or equivalent (See 8.2). Product shall not be rejected on the basis of hardness if the tensile properties of 3.4.1.1, determined on specimens taken from the same sample as that with nonconforming hardness or from another sample with similar nonconforming hardness, are acceptable.
- 3.4.1.2.1 Bars: 170 to 255 HB, determined at approximate mid-radius or quarter-thickness.
- 3.4.1.2.2 Forgings, Extrusions, and Flash Welded Rings: Not higher than 240 HB.
- 3.4.1.2.3 Mechanical Tubing: Not higher than 100 HRB, determined approximately midway between outer and inner surfaces.
- 3.4.1.3 Susceptibility to Intergranular Attack: Specimens from the product shall pass the intergranular corrosion test performed in accordance with ASTM A 262, Practice E.
- 3.4.2 Forging Stock: When a sample of stock is forged to a test coupon and heat treated as in 3.3, specimens taken from the heat treated coupon shall conform to the requirements of 3.4.1.1.2 and 3.4.1.2. If specimens taken from the stock after heat treatment as in 3.3 conform to the requirements of 3.4.1.1.2 and 3.4.1.2, the tests shall be acceptable as equivalent to tests of a forged coupon.

3.4.3 Stock for Extruding or Flash Welded Rings: Specimens taken from the stock after heat treatment as in 3.3 shall conform to the requirements of 3.4.1.1.2 and 3.4.1.2.

3.5 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

3.6 Tolerances:

Shall conform to all applicable requirements of the following:

3.6.1 Bars and Wire: AMS 2241 or MAM 2241.

3.6.2 Mechanical Tubing: AMS 2243 or MAM 2243.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: The following requirements are acceptance tests and shall be performed on each heat or lot as applicable:

4.2.1.1 Composition (3.1) of each heat.

4.2.1.2 Tensile properties (3.4.1.1.1 or 3.4.1.1.2) of each lot of bars, wire, forgings, extrusions, mechanical tubing, and flash welded rings.

4.2.1.3 Hardness (3.4.1.2) of each lot of bars, forgings, extrusions, mechanical tubing, and flash welded rings.

4.2.1.4 Tolerances (3.6) of bars, wire, and mechanical tubing.

4.2.2 Periodic Tests: Susceptibility to intergranular attack (3.4.1.3), tests of forging stock (3.4.2) and stock for extruding or flash welded rings (3.4.3) to demonstrate ability to develop required properties, and grain flow of die forgings (3.5.1) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be as follows:

4.3.1 Bars, Wire, Extrusions, Mechanical Tubing, Flash Welded Rings, and Stock for Forging, Extruding, or Flash Welded Rings: In accordance with AMS 2371.

4.3.2 Forgings: In accordance with AMS 2374.

4.4 Reports:

4.4.1 The vendor of bars, wire, forgings, extrusions, mechanical tubing, and flash welded rings shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile properties or hardness of each lot and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS 5848B, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.4.2 The vendor of stock for forging, extruding, or flash welded rings shall furnish with each shipment a report showing the results of tests for chemical composition of each heat. This report shall include the purchase order number, heat number, AMS 5848B, size, and quantity.

4.5 Resampling and Retesting:

Shall be as follows:

4.5.1 Bars, Wire, Extrusions, Mechanical Tubing, Flash Welded Rings, and Stock for Forging, Extruding, or Flash Welded Rings: In accordance with AMS 2371.

4.5.2 Forgings: In accordance with AMS 2374.

5. PREPARATION FOR DELIVERY:

5.1 Sizes:

Except when exact lengths or multiples of exact lengths are ordered, straight bars, wire, and tubing will be acceptable in mill lengths of 6 to 20 feet (1.8 to 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 feet (3 m).