

AEROSPACE MATERIAL SPECIFICATION

An American National Standard

SAE AMS 7819B

Issued 1-31-64
Revised 7-1-86

Superseding AMS 7819A

MOLYBDENUM ALLOY BARS
0.48Ti - 0.09Zr - 0.02C
Arc Cast, Stress Relieved

UNS R03640

1. SCOPE:

1.1 Form: This specification covers an arc-cast molybdenum alloy in the form of round bars.

1.2 Application: Primarily for parts requiring high modulus and uniform strength up to 2300°F (1260°C). This alloy is not recommended for use in oxidizing atmospheres above 1000°F (540°C) unless protected by a suitable coating.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E8 - Tension Testing of Metallic Materials

ASTM E92 - Vickers Hardness of Metallic Materials

ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

2.4 ANSI Publications: Available from American National Standards Institute, 1430 Broadway, New York, NY 10018.

ANSI B46.1 - Surface Texture

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight; carbon shall be determined in accordance with ASTM E350, molybdenum by difference, gaseous elements by vacuum fusion, and other metallic elements by spectrographic or other analytical methods approved by purchaser:

	min	max	Check Analysis	
			Under Min	Over Max
Molybdenum	99.25	--	--	--
Titanium	0.40	- 0.55	0.05	0.05
Zirconium	0.06	- 0.12	0.02	0.02
Carbon	0.010	- 0.030	0.005	0.005
Iron	--	0.020	--	0.002
Silicon	--	0.010	--	0.002
Nickel	--	0.010	--	0.001
Oxygen	--	0.0030 (30 ppm)	--	--
Nitrogen	--	0.0010 (10 ppm)	--	0.0005 (5 ppm)
Hydrogen	--	0.0005 (5 ppm)	--	--

3.2 Condition: Hot-cold worked, descaled, and stress-relieved; when so specified, bars shall be centerless ground before being stress-relieved. The surface texture of centerless ground bars shall be 90 microin. (2.3 μm) or smoother, determined in accordance with ANSI B46.1.

3.3 Properties: Bars 0.125 to 4.500 in. (3.00 to 112.50 mm), incl, in nominal diameter shall conform to the following requirements; bars under 0.125 in. (3.00 mm) or over 4.500 in. (112.50 mm) in nominal diameter shall have tensile properties and hardness as agreed upon by purchaser and vendor:

3.3.1 As-Received:

3.3.1.1 Tensile Properties: Shall be as specified in Table I, determined in accordance with ASTM E8 with the rate of strain maintained at 0.002 - 0.005 in./in. per min. (0.002 - 0.005 mm/mm per min.) through the 0.6% offset and 0.002 - 0.05 in./in. per min. (0.02 - 0.05 mm/mm per min.) above the 0.6% offset to fracture.

3.3.1.1 (Continued):

TABLE I

Nominal Diameter Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 4D %, min
0.125 to 0.875, incl	115,000	100,000	18
Over 0.875 to 1.875, incl	100,000	85,000	10
Over 1.875 to 2.875, incl	90,000	80,000	10
Over 2.875 to 3.500, incl	85,000	75,000	5
Over 3.500 to 4.500, incl	80,000	70,000	5

TABLE I (SI)

Nominal Diameter Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 4D %, min
3.00 to 22.00, incl	795	690	18
Over 22.00 to 47.00, incl	690	585	10
Over 47.00 to 72.00, incl	620	550	10
Over 72.00 to 87.50, incl	585	515	5
Over 87.50 to 112.50, incl	550	485	5

3.3.1.2 Hardness: Shall be as follows, determined in accordance with ASTM E92:

Nominal Diameter		Maximum Hardness HV/10
Inches	Millimetres	
0.125 to 0.875, incl	3.00 to 22.00, incl	320
Over 0.875 to 1.125, incl	Over 22.00 to 28.00, incl	310
Over 1.125 to 1.875, incl	Over 28.00 to 47.00, incl	300
Over 1.875 to 2.875, incl	Over 47.00 to 72.00, incl	290
Over 2.875 to 3.500, incl	Over 72.00 to 87.50, incl	285
Over 3.500 to 4.500, incl	Over 87.50 to 112.50, incl	280

3.3.2 After High-Temperature Exposure: Bars shall meet the tensile property (3.3.1.1) and hardness (3.3.1.2) requirements after being heated in a suitable protective atmosphere to $2100^{\circ}\text{F} \pm 25$ ($1150^{\circ}\text{C} \pm 15$), held at heat for 30 min. ± 3 , and cooled rapidly.3.4 Quality:

3.4.1 Alloy shall be carbon deoxidized and vacuum arc melted using consumable electrode practice.

3.4.2 Bars, as received by purchaser, shall be uniform in quality and condition, sound, smooth, and free from foreign materials and from imperfections detrimental to usage of the bars.

3.5 Tolerances: Shall be as follows:

3.5.1 Hot-Cold Worked and Descaled: Shall be as shown in Table II.

TABLE II

Nominal Diameter Inches	Tolerance, Inch		Out of Round Inch
	plus	minus	
0.125 to 0.281, incl	0.002	0.002	0.004
Over 0.281 to 0.406, incl	0.003	0.003	0.006
Over 0.406 to 0.625, incl	0.010	0.005	0.012
Over 0.625 to 0.875, incl	0.015	0.005	0.015
Over 0.875 to 1.000, incl	0.020	0.005	0.015
Over 1.000 to 1.375, incl	0.020	0.010	0.018
Over 1.375 to 1.500, incl	0.020	0.015	0.020
Over 1.500 to 1.625, incl	0.025	0.015	0.020
Over 1.625 to 2.000, incl	0.030	0.020	0.025
Over 2.000 to 2.500, incl	0.032	0.032	0.025
Over 2.500 to 3.250, incl	0.032	0.032	0.027
Over 3.250 to 3.500, incl	0.045	0.045	0.040
Over 3.500 to 4.500, incl	0.062	0.062	0.050

TABLE II (SI)

Nominal Diameter Millimetres	Tolerance, Millimeters		Out of Round Millimetres
	plus	minus	
3.00 to 7.00, incl	0.05	0.05	0.10
Over 7.00 to 10.00, incl	0.08	0.08	0.15
Over 10.00 to 15.00, incl	0.25	0.12	0.30
Over 15.00 to 22.00, incl	0.38	0.12	0.38
Over 22.00 to 25.00, incl	0.50	0.12	0.38
Over 25.00 to 34.00, incl	0.50	0.25	0.45
Over 34.00 to 37.50, incl	0.50	0.38	0.50
Over 37.50 to 40.00, incl	0.62	0.38	0.50
Over 40.00 to 50.00, incl	0.75	0.50	0.62
Over 50.00 to 62.50, incl	0.80	0.80	0.62
Over 62.50 to 81.00, incl	0.80	0.80	0.68
Over 81.00 to 87.50, incl	1.12	1.12	1.00
Over 87.50 to 112.50, incl	1.55	1.55	1.25

3.5.2 Centerless Ground:

Nominal Diameter		Tolerance, Plus and Minus	
Inches	Millimetres	Inch	Millimetre
0.0625 to 2.000, incl	1.500 to 50.00, incl	0.002	0.05
Over 2.000	Over 50.00	0.003	0.08

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of bars shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the bars conform to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), tensile properties (3.3.1.1), hardness (3.3.1.2), and tolerances (3.5) are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for tensile properties and hardness after high-temperature exposure (3.3.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling: Shall be as follows; a lot shall be all bars of the same nominal size from the same heat, processed at the same time, and presented for vendor's inspection at one time:

4.3.1 Acceptance Tests:

4.3.1.1 Composition: One specimen from each heat.

4.3.1.2 Tensile and Hardness Tests: One specimen from each lot.

4.3.1.2.1 Specimens for tensile testing shall be taken from the center of bars up to 1.125 in. (28.00 mm) in nominal diameter and at mid-radius of larger bars.

4.3.2 Periodic Tests: As agreed upon by purchaser and vendor.

4.4 Reports:

4.4.1 The vendor of bars shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile properties and hardness of each lot. This report shall include the purchase order number, heat number, AMS 7819B, size, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 7819B, contractor or other direct supplier of bars, part number, and quantity. When bars for making parts are produced or purchased by the parts vendor, that vendor shall inspect each lot of bars to determine conformance to the requirements of this specification and shall include in the report either a statement that the bars conform or copies of laboratory reports showing the results of tests to determine conformance.