

AEROSPACE STANDARD AMENDMENT

SAE AS85049A-A2

Issued 2004-08

Connector Accessories, Electrical General Specification For

Present Requirement: 3.3.7 Finish:

- Page 13 1/ W-Cadmium – Olive drab over suitable underplate, 1000 hour salt spray (see 3.5.3).
B- Black Cadmium – In accordance with AMS-QQ-P-416, Type II, Class 3.

- Page 14 J -Olive drab cadmium plate in accordance with AMS-QQ-P-416 over a suitable underplate to withstand 2000 hour salt spray (see 3.5.3). Final finish shall be electrically conductive.

Change Requirement: 3.3.7 Finish:

- Page 13 1/ 2/ W-Cadmium – Olive drab over suitable underplate, 1000 hour salt spray (see 3.5.3).
2/ B-Black Cadmium – In accordance with AMS-QQ-P-416, Type II, Class 3.
- Page 14 2/ J-Olive drab cadmium plate in accordance with AMS-QQ-P-416 over a suitable underplate to withstand 2000 hour salt spray (see 3.5.3). Final finish shall be electrically conductive.
- 2/ This document includes cadmium as a plating material. The use of cadmium has been restricted and/or banned for use in many countries due to environmental and health concerns. The user should consult with local officials on applicable health and environmental regulations regarding its use. "User" in the context of this warning refers to manufacturers that apply cadmium plating to the subject parts.

Rationale for Change: To advise potential users of the environmental issues associated with the use of cadmium.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2003 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER:
Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org
SAE WEB ADDRESS: <http://www.sae.org>